



中国认可
国际互认
检测
TESTING
CNAS L6478



TEST REPORT

Report No. : WTF24F06131085T
Applicant..... : Mid Ocean Brands B.V.
Address..... : 7/F., Kings Tower, 111 King Lam Street, Cheung Sha
Wan, Kowloon, Hong Kong
Manufacturer : 106613
Sample Name : Bottle with wireless speaker
Sample Model..... : MO2312
Test Requested : In accordance with Regulation (EU) No 10/2011, Council
of Europe Resolution CM/Res(2013)9, French Décret
n°2007-766, with amendments and Regulation (EC) No
1935/2004.
Test Conclusion : **Pass**(Please refer to next pages for details)
Date of Receipt sample : 2024-06-05
Testing period : 2024-06-05 to 2024-06-18
Date of Issue..... : 2024-06-19
Test Result..... : Refer to next page (s)

Prepared By:

Waltek Testing Group (Foshan) Co., Ltd.

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City,
Chencun, Shunde District, Foshan, Guangdong, China
Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Signed for and on behalf of
Waltek Testing Group (Foshan) Co., Ltd.

Jessise Liu

Jessise.Liu



Report No.: WTF24F06131085T

Test Results:

1. Council of Europe Resolution CM/Res(2013)9-Specific Migration of Heavy Metal

Test Items	1st+2nd Migration (mg/kg)		LOQ (mg/kg)	Limit (mg/kg)
	No.1			
Aluminium (Al)	ND		0.2	35
Antimony (Sb)	ND		0.02	0.28
Chromium (Cr)	ND		0.04	1.75
Cobalt (Co)	ND		0.02	0.14
Copper (Cu)	ND		0.2	28
Iron (Fe)	0.8		0.4	280
Manganese (Mn)	ND		0.2	12.6
Molybdenum (Mo)	ND		0.02	0.84
Nickel (Ni)	ND		0.02	0.98
Silver (Ag)	ND		0.02	0.56
Tin (Sn)	ND		0.2	700
Vanadium (V)	ND		0.01	0.07
Zinc (Zn)	ND		0.2	35
Arsenic (As)	ND		0.002	0.014
Barium (Ba)	ND		0.2	8.4
Beryllium (Be)	ND		0.01	0.07
Cadmium (Cd)	ND		0.002	0.035
Lead (Pb)	ND		0.01	0.07
Lithium (Li)	ND		0.01	0.336
Mercury (Hg)	ND		0.002	0.021
Thallium (Tl)	ND		0.0002	0.0007
Magnesium (Mg)	ND		0.2	--
Titanium (Ti)	ND		0.02	--



Report No.: WTF24F06131085T

Test Items	3rd Migration (mg/kg)	LOQ (mg/kg)	Limit (mg/kg)
	No.1		
Aluminium (Al)	ND	0.1	5
Antimony (Sb)	ND	0.01	0.04
Chromium (Cr)	ND	0.02	0.25
Cobalt (Co)	ND	0.01	0.02
Copper (Cu)	ND	0.1	4
Iron (Fe)	0.3	0.2	40
Manganese (Mn)	ND	0.1	1.8
Molybdenum (Mo)	ND	0.01	0.12
Nickel (Ni)	ND	0.01	0.14
Silver (Ag)	ND	0.01	0.08
Tin (Sn)	ND	0.1	100
Vanadium (V)	ND	0.005	0.01
Zinc (Zn)	ND	0.1	5
Arsenic (As)	ND	0.001	0.002
Barium (Ba)	ND	0.1	1.2
Beryllium (Be)	ND	0.005	0.01
Cadmium (Cd)	ND	0.001	0.005
Lead (Pb)	ND	0.005	0.01
Lithium (Li)	ND	0.005	0.048
Mercury (Hg)	ND	0.001	0.003
Thallium (Tl)	ND	0.0001	0.0001
Magnesium (Mg)	ND	0.1	--
Titanium (Ti)	ND	0.01	--

Note:

1. Test Method: With reference to BS EN 13130-1: 2004, analysis was performed by ICP-MS.
2. Test Condition and simulant: Sample(s) were migrated with 5g/L citric acid at 70°C for 2 hours.
3. "mg/kg" = milligram per kilogram of foodstuff in contact with
4. LOQ = Limit of quantitation
5. ND = Not Detected or lower than limit of quantitation
6. "--" = Not regulated
7. The specification was quoted from Technical Guide on Metals and alloys used in food contact materials of Council of Europe Resolution CM/Res(2013)9.



Report No.: WTF24F06131085T

2. Overall Migration Test

Food Simulant	Test Condition	Result (mg/dm ²)			LOQ (mg/dm ²)	Limit (mg/dm ²)
		No.2				
		1 st Migration	2 nd Migration	3 rd Migration		
3% Acetic Acid	70°C for 2 hours	ND	ND	ND	3.0	3 rd Migration:10, 3 rd <2 nd <1 st
50% Ethanol	70°C for 2 hours	ND	ND	ND	3.0	3 rd Migration:10, 3 rd <2 nd <1 st

Note:

1. Test method: With reference to BS EN 1186-1: 2002, BS EN 1186-2: 2022, BS EN 1186-3: 2022
2. "mg/dm²" = milligram per square decimetre
3. "°C" = Celsius degree
4. ND = Not Detected or lower than limit of quantitation
5. The specification was quoted from (EU) No 10/2011 and its amendments (EU) 2016/1416, (EU) 2017/752, (EU)2019/37 and (EU) 2020/1245.

Food Simulant	Test Condition	Result (mg/kg)	LOQ(mg/kg)	Limit (mg/kg)
		No.3		
3% Acetic Acid	70°C for 2 hours	ND	20	60
50% Ethanol	70°C for 2 hours	ND	20	60

Note:

1. Test method: With reference to EN 1186-1: 2002, EN 1186-2: 2022, EN 1186-3: 2022
2. "mg/kg" = milligram per kilogram of foodstuff in contact with
3. "°C" = Celsius degree
4. LOQ = Limit of quantitation
5. ND = Not Detected or lower than limit of quantitation
6. The specification was quoted from Council of Europe Resolution AP(2004)5 and French Arrêté du 25 novembre 1992 for Silicone Elastomers.



Report No.: WTF24F06131085T

3. Specific Migration of heavy metal

Test Items	Result(mg/kg)			LOQ (mg/kg)	Limit (mg/kg)	
	No.2					
	1 st Migration	2 nd Migration	3 rd Migration			
Nickel (Ni)	ND	ND	ND	0.01	3 rd Migration:0.02, 3 rd <2 nd <1 st	
Aluminium (Al)	ND	ND	ND	0.1	3 rd Migration:1 3 rd <2 nd <1 st	
Barium (Ba)	ND	ND	ND	0.1	3 rd Migration:1 3 rd <2 nd <1 st	
Cobalt (Co)	ND	ND	ND	0.01	3 rd Migration:0.05 3 rd <2 nd <1 st	
Copper (Cu)	ND	ND	ND	0.1	3 rd Migration:5 3 rd <2 nd <1 st	
Iron (Fe)	ND	ND	ND	0.1	3 rd Migration:48 3 rd <2 nd <1 st	
Lithium (Li)	ND	ND	ND	0.01	3 rd Migration:0.6 3 rd <2 nd <1 st	
Manganese (Mn)	ND	ND	ND	0.01	3 rd Migration:0.6 3 rd <2 nd <1 st	
Zinc (Zn)	ND	ND	ND	0.1	3 rd Migration:5 3 rd <2 nd <1 st	
Antimony (Sb)	ND	ND	ND	0.01	3 rd Migration:0.04 3 rd <2 nd <1 st	
Arsenic (As)	ND	ND	ND	0.01	Not detected	
Cadmium (Cd)	ND	ND	ND	0.002	Not detected	
Chromium (Cr)	ND	ND	ND	0.01	Not detected	
Mercury (Hg)	ND	ND	ND	0.01	Not detected	
Lead (Pb)	ND	ND	ND	0.01	Not detected	
Europeum (Eu)	ND	ND	ND	0.02	3 rd Migration:0.05 3 rd <2 nd <1 st	Sum< 0.05
Gadolinium (Gd)	ND	ND	ND	0.02	3 rd Migration:0.05 3 rd <2 nd <1 st	
Lanthanum (La)	ND	ND	ND	0.02	3 rd Migration:0.05 3 rd <2 nd <1 st	
Terbium (Tb)	ND	ND	ND	0.02	3 rd Migration:0.05 3 rd <2 nd <1 st	



Report No.: WTF24F06131085T

Note:

1. Test Method: With reference to BS EN 13130-1: 2004, sample preparation in 3% acetic acid at 70°C for 2 hours, analysis was performed by ICP-MS.
2. "mg/kg" = milligram per kilogram of foodstuff in contact with
3. ND = Not Detected or lower than limit of quantitation
4. The specification was quoted from (EU) No 10/2011 and its amendments (EU) 2016/1416, (EU) 2017/752 and (EU) 2020/1245.

4. Specific Migration of Primary Aromatic Amines

Test Item	Result (mg/kg)			LOQ (mg/kg)	Limit (mg/kg)
	No.2				
	1 st Migration	2 nd Migration	3 rd Migration		
Migration of Primary aromatic amines	ND	ND	ND	0.01	Not detected

Note:

1. Test Method: With reference to § 64 LFGB L No. 00.00-6, analysis was performed by UV-visible Spectrometer.
2. Test Condition and simulant: 3% acetic acid at 70°C for 2 hours
3. "mg/kg" = milligram per kilogram of foodstuff in contact with
4. ND = Not Detected or lower than limit of quantitation
5. The specification was quoted from (EU) No 10/2011 and its amendments (EU) 2016/1416, (EU) 2017/752 and (EU) 2020/1245.



Report No.: WTF24F06131085T

5. Specific Migration of Primary Aromatic Amines (single substance)*

Test Items	CAS No.	Result(mg/kg)			LOQ (mg/kg)	Limit (mg/kg)
		No.2				
		1 st Migration	2 nd Migration	3 rd Migration		
2-methoxyaniline	90-04-0	ND	ND	ND	0.002	Not Detected
4,4'-Diaminobiphenyl	92-87-5	ND	ND	ND	0.002	Not Detected
4,4'-Methylen-bis-(2-chloroaniline)	101-14-4	ND	ND	ND	0.002	Not Detected
4,4'-Diaminodiphenylmethane	101-77-9	ND	ND	ND	0.002	Not Detected
4,4'-Oxydianiline	101-80-4	ND	ND	ND	0.002	Not Detected
4-chloroaniline	106-47-8	ND	ND	ND	0.002	Not Detected
3,3'-Dimethoxybenzidine	119-90-4	ND	ND	ND	0.002	Not Detected
3,3'-Dimethylbenzidine	119-93-7	ND	ND	ND	0.002	Not Detected
2-Methoxy-5-methylaniline	120-71-8	ND	ND	ND	0.002	Not Detected
2,4,5 – Trimethylaniline	137-17-7	ND	ND	ND	0.002	Not Detected
4,4'-Thiodianiline	139-65-1	ND	ND	ND	0.002	Not Detected
4-aminoazobenzene	60-09-3	ND	ND	ND	0.002	Not Detected
2,4-diaminoanisol	615-05-4	ND	ND	ND	0.002	Not Detected
4,4'-diamino-3,3'-dimethyldiphenylmethane	838-88-0	ND	ND	ND	0.002	Not Detected
2-Naphthylamine	91-59-8	ND	ND	ND	0.002	Not Detected
3,3'-Dichlorobenzidine	91-94-1	ND	ND	ND	0.002	Not Detected
4-Aminobiphenyl	92-67-1	ND	ND	ND	0.002	Not Detected
2-methylaniline	95-53-4	ND	ND	ND	0.002	Not Detected
4-chloro-o-Toluidine	95-69-2	ND	ND	ND	0.002	Not Detected
2,4-Toluyldiamine	95-80-7	ND	ND	ND	0.002	Not Detected
2,4-Aminoazotoluene	97-56-3	ND	ND	ND	0.002	Not Detected
2-Amino-4-nitrotoluene	99-55-8	ND	ND	ND	0.002	Not Detected
2,4-Xylidin	95-68-1	ND	ND	ND	0.002	Not Detected
2,6-Xylidin	87-62-7	ND	ND	ND	0.002	Not Detected
1, 3 - phenylene diamine	108-45-2	ND	ND	ND	0.002	Not Detected

Note:

1. Test Method: With reference to EN 13130-1:2004, analysis was performed by LC-MS-MS.
2. Test Condition and simulant: 3% acetic acid at 70°C for 2 hours.
3. "mg/kg" = milligram per kilogram of foodstuff in contact with.
4. ND = Not Detected or lower than limit of quantitation.
5. The specification was quoted from (EU) No 10/2011 and its amendment (EU) 2020/1245.
6. The testing item marked with "*" does not been accredited by CNAS.



Report No.: WTF24F06131085T

6. Bisphenol A Content*

Test Item	Result (mg/kg)		LOQ (mg/kg)	Limit (mg/kg)
	No.2	No.3		
Bisphenol A	ND	ND	0.1	Not Detected (<0.1mg/kg)

Note:

1. Test Method: With reference to EPA3550C:2007, analysis was performed by GC-MS.
2. "mg/kg" = milligram per kilogram
3. LOQ = Limit of quantitation
4. ND = Not Detected or lower than limit of quantitation
5. The specification was quoted from Law No 2012-1442.
6. The testing item marked with "*" does not been accredited by CNAS.

7. Peroxide Value Test*

Test Item	Result	Limit
	No.3	
Peroxide Value	Absent	Absent

Note:

1. Test method: With reference to French pharmacopoeia Xth edition.
2. The specification was quoted from French Arrêté du 25 novembre 1992 for Silicone Elastomers.
3. The testing item marked with "*" does not been accredited by CNAS.

8. Volatile Organic Compounds

Test Item	Test Condition	Result (%)	LOQ (%)	Limit (%)
		No.3		
Volatile Organic compounds	200°C for 4 hours	0.44	0.05	0.5

Note:

1. Test method: With reference to French Arrêté du 25 novembre 1992 Annex III for silicone Elastomers.
2. "%" = percentage by weight
3. LOQ = Limit of quantitation
4. The specification was quoted from French Arrêté du 25 novembre 1992 for Silicone Elastomers.



Report No.: WTF24F06131085T

9. Specific Migration of Organotin (as Tin)

Food Simulant	Test Condition	Result (mg/kg)		
		No.3	LOQ (mg/kg)	Limit (mg/kg)
3% acetic acid	70°C for 2 hours	ND	0.01	0.1

Note:

1. Test Method: With reference to BS EN 13130-1: 2004, analysis was performed by ICP-MS.
2. "mg/kg" = milligram per kilogram
3. LOQ = Limit of quantitation
4. ND = Not Detected, less than LOQ
5. The specification was quoted from French Arrêté du 25 novembre 1992 for Silicone Elastomers.

10. Specific Migration of Bisphenol A

Test Item	Result (mg/kg)			LOQ (mg/kg)	Limit (mg/kg)
	No.3				
	1 st Migration	2 nd Migration	3 rd Migration		
Migration of Bisphenol A	ND	ND	ND	0.01	3 rd Migration:0.05 3 rd < 2 nd < 1 st

Note:

1. Test Method: With reference to CEN/TS 13130-13-2005, sample preparation in 3% acetic acid at 40°C for 2 hours.
2. "mg/kg" = milligram per kilogram
3. LOQ = Limit of quantitation
4. ND = Not Detected or lower than limit of quantitation
5. The specification was quoted from regulation (EU) No 10/2011 with its amendments (EU) 2018/213 and (EU) 2020/1245.



Report No.: WTF24F06131085T

Sample Photo:





Photograph of parts tested:

No.	Photo of testing part	Parts Description	Client Claimed Material
1		Silver metal	Stainless steel



Report No.: WTF24F06131085T

No.	Photo of testing part	Parts Description	Client Claimed Material
2		Black plastic	PP
3		Transparent silicone rubber	Silicone rubber

Remarks:

1. The results shown in this test report refer only to the sample(s) tested;
2. This test report cannot be reproduced, except in full, without prior written permission of the company;
3. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver;
4. The Applicant name and Address, the sample(s) and sample information was/were provided by the applicant who should be responsible for the authenticity which Waltek hasn't verified;
5. If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.

===== End of Report =====