

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 1 of 25

Client : Mid Ocean Brands B.V.

Address : 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong

The following merchandise was (were) submitted and identified by the client as:

Name of Product : Toddler's sippy cup in Tritan

Test Model : MO2330

Model May Cover : /

Main Material: tritan, PP, silicone

Supplier: 118518

Buyer: Mid Ocean Brands B.V.

Labeled Age Grading: 6+ months

Applicant's Specified

Age Group for Testing : 6+ months

Age Grading for Test: 6+ months

Sample Received : Apr. 29, 2024  
May. 13, 2024

Test Period : Apr. 29, 2024 - May. 11, 2024  
May. 13, 2024 - May. 22, 2024

Test Specification and Conclusion:

Please refer to next page


Prepared By :



David Chen

Testing Engineer

Reviewed By :



Dora Cheng

Reporter Supervisor

Issued By :



Ada Wang

Lab Manager



SZ2024041281-1E

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhong Road, High-new district, Suzhou, China 215129

Tel: +86(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May, 22, 2024

Page No.: 2 of 25

Test Specification		Conclusion
1.	Total Lead(Pb) content according to EC Regulation 1907/2006, REACH Annex XVII (entry 63)	PASS
2.	Total Cadmium(Cd) content according to EC Regulation 1907/2006, REACH Annex XVII (entry 23)	PASS
3.	Phthalates content according to EC Regulation 1907/2006, REACH Annex XVII (entry 51&52)	PASS
4.	Polycyclic Aromatic Hydrocarbons (PAHs) content according to EC Regulation 1907/2006, (EU) No 1272/2013 Amending PAHs of REACH Annex XVII(entry 50)	PASS
5.	Child care articles- Drinking equipment-Safety requirements and Test methods- EN 14350:2020+A1:2023	PASS
6.	Migration of certain elements according to EN 14350:2020+A1:2023	PASS
7.	Volatile organic compounds content according to EN 14350:2020+A1:2023	PASS
8.	Colour fastness according to EN 14350:2020+A1:2023	PASS
9.	N-Nitrosamine and N-Nitrosatable Content according to EN 14350:2020+A1:2023	PASS
10	Extractable Formaldehyde content according to EN 14350:2020+A1:2023	PASS
Commission Regulation (EU) No 10/2011 and its subsequent amendment Regulation EU No.1282/2011, 1183/2012, 202/2014 and Regulation (EU) 2016/1416, (EU) 2017/752, (EU) 2018/213, (EU) 2020/1245 on plastic materials and articles intended to come into contact with foodstuffs, General Requirement(Article 3) in EU Regulation No. 1935/2004 & EN 14350:2020+A1:2023		
11.	Overall Migration test for Plastic	PASS
12.	Soluble Heavy Metals for Plastic	PASS
13.	Specific Migration of Primary Aromatic Amine for Plastic	PASS
14.	Specific Migration of Bisphenol-A for Plastic	PASS
15.	Bisphenol-A (BPA) Content for Plastic	PASS
French Decree No. 2007-766 of 10 May 2007 and its amendment, French Order of 25 November 1992, General Requirement (Article 3) in EU Regulation No. 1935/2004 & EN 14350:2020+A1:2023		
11.	Overall Migration test for Silicone rubber	PASS
14.	Specific Migration of Bisphenol-A for Silicone rubber	PASS
15.	Bisphenol-A (BPA) Content for Silicone rubber	PASS
16.	Volatile Organic Matter (VOM) for Silicone rubber	PASS
17.	Peroxide value for Silicone rubber	PASS
18.	Specific migration of organotin (as Tin) for Silicone rubber	PASS

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel: +86(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 3 of 25

## TEST RESULTS:

### 1. Total Lead(Pb) Content

**Test Method:** With reference to EPA 3052-1996 & EPA 6010D-2018, Analysis was performed by ICP-OES.

Test Item(s)	MDL (mg/kg)	Test Result(s) (mg/kg)		Limited Value <sup>①</sup> (mg/kg)
		1#+2#	3#+4#+5#	
Total Lead(Pb)	10	N.D.	N.D.	500

Test Item(s)	MDL (mg/kg)	Test Result(s) (mg/kg)		Limited Value <sup>①</sup> (mg/kg)
		6#		
Total Lead(Pb)	10	N.D.		500

**Remark:** <sup>①</sup>The Limited value is based on EC Regulation 1907/2006, REACH Annex XVII (entry 63).

### 2. Total Cadmium(Cd) Content

**Test Method:** With reference to EN 1122- 2001 Method B, Analysis was performed by ICP-OES.

Test Item(s)	MDL (mg/kg)	Test Result(s) (mg/kg)		Limited Value <sup>②</sup> (mg/kg)
		1#+2#		
Total Cadmium(Cd)	10	N.D.		100

**Test Method:** With reference to EPA 3052-1996 & EPA 6010D-2018, Analysis was performed by ICP-OES.

Test Item(s)	MDL (mg/kg)	Test Result(s) (mg/kg)		Limited Value <sup>②</sup> (mg/kg)
		3#+4#+5#	6#	
Total Cadmium(Cd)	10	N.D.	N.D.	100

**Remark:** <sup>②</sup>The Limited value is based on EC Regulation 1907/2006, REACH Annex XVII (entry 23).

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel: +86/(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 4 of 25

### 3. Phthalates Content

**Test Method:** With reference to EN 14372:2004, Analysis was performed by GC-MS.

(1-1) For plasticized materials (including toys and childcare articles)

Test Item(s)	Unit	MDL	Test Result(s)	Limited Value <sup>®</sup>
			1#+2#	
Dibutyl Phthalate(DBP)	%	0.005	N.D.	---
Benzylbutyl Phthalate(BBP)		0.005	N.D.	---
Di-(2-ethylhexyl)Phthalate(DEHP)		0.005	N.D.	---
Di-isobutyl phthalate (DIBP)		0.005	N.D.	---
Total (DBP+BBP+DEHP+DIBP)		---	< 0.020	< 0.1

(1-2) For toys and childcare articles that can be mouthed

Test Item(s)	Unit	MDL	Test Result(s)	Limited Value <sup>®</sup>
			1#+2#	
Di-iso-nonylphthalate(DINP)	%	0.005	N.D.	---
Di-n-octylphthalate(DNOP)		0.005	N.D.	---
Di-iso-decylphthalate(DIDP)		0.005	N.D.	---
Total (DINP+DNOP+DIDP)		---	< 0.015	< 0.1

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel: +86/(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 5 of 25

(1-1) For plasticized materials (including toys and childcare articles)

Test Item(s)	Unit	MDL	Test Result(s)	Limited Value <sup>③</sup>
			3#+4#+5#	
Dibutyl Phthalate(DBP)	%	0.005	N.D.	---
Benzylbutyl Phthalate(BBP)		0.005	N.D.	---
Di-(2-ethylhexyl)Phthalate(DEHP)		0.005	N.D.	---
Di-isobutyl phthalate (DIBP)		0.005	N.D.	---
Total (DBP+BBP+DEHP+DIBP)		---	< 0.020	< 0.1

(1-2) For toys and childcare articles that can be mouthed

Test Item(s)	Unit	MDL	Test Result(s)	Limited Value <sup>③</sup>
			3#+4#+5#	
Di-iso-nonylphthalate(DINP)	%	0.005	N.D.	---
Di-n-octylphthalate(DNOP)		0.005	N.D.	---
Di-iso-decylphthalate(DIDP)		0.005	N.D.	---
Total (DINP+DNOP+DIDP)		---	< 0.015	< 0.1

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel: +86/(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 6 of 25

(1-1) For plasticized materials (including toys and childcare articles)

Test Item(s)	Unit	MDL	Test Result(s)	Limited Value <sup>③</sup>
			6#	
Dibutyl Phthalate(DBP)	%	0.005	N.D.	---
Benzylbutyl Phthalate(BBP)		0.005	N.D.	---
Di-(2-ethylhexyl)Phthalate(DEHP)		0.005	N.D.	---
Di-isobutyl phthalate (DIBP)		0.005	N.D.	---
Total (DBP+BBP+DEHP+DIBP)		---	< 0.020	< 0.1

(1-2) For toys and childcare articles that can be mouthed

Test Item(s)	Unit	MDL	Test Result(s)	Limited Value <sup>③</sup>
			6#	
Di-iso-nonylphthalate(DINP)	%	0.005	N.D.	---
Di-n-octylphthalate(DNOP)		0.005	N.D.	---
Di-iso-decylphthalate(DIDP)		0.005	N.D.	---
Total (DINP+DNOP+DIDP)		---	< 0.015	< 0.1

**Remark:** <sup>③</sup>The Limited value is based on EC Regulation 1907/2006, REACH Annex XVII (entry 51&52).

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel: +86/(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 7 of 25

## 4. Polycyclic Aromatic Hydrocarbons (PAHs) Content

**Test Method:** With reference to AfPS GS 2019:01 PAK, Analysis was performed by GC-MS.

Test Item(s)	CAS No.	MDL (mg/kg)	Test Result(s) (mg/kg)	Limited Value <sup>④</sup> (mg/kg)	
			1#+2#	Category I	Category II
Benzo[a]pyrene	50-32-8	0.1	N.D.	1	0.5
Benzo[e]pyrene	192-97-2	0.1	N.D.	1	0.5
Benzo[a]anthracene	56-55-3	0.1	N.D.	1	0.5
Chrysene	218-01-9	0.1	N.D.	1	0.5
Benzo[b]fluoranthene	205-99-2	0.1	N.D.	1	0.5
Benzo[j]fluoranthene	205-82-3	0.1	N.D.	1	0.5
Benzo[k]fluoranthene	207-08-9	0.1	N.D.	1	0.5
Dibenzo[a,h]anthracene	53-70-3	0.1	N.D.	1	0.5

Test Item(s)	CAS No.	MDL (mg/kg)	Test Result(s) (mg/kg)	Limited Value <sup>④</sup> (mg/kg)	
			3#+4#+5#	Category I	Category II
Benzo[a]pyrene	50-32-8	0.1	N.D.	1	0.5
Benzo[e]pyrene	192-97-2	0.1	N.D.	1	0.5
Benzo[a]anthracene	56-55-3	0.1	N.D.	1	0.5
Chrysene	218-01-9	0.1	N.D.	1	0.5
Benzo[b]fluoranthene	205-99-2	0.1	N.D.	1	0.5
Benzo[j]fluoranthene	205-82-3	0.1	N.D.	1	0.5
Benzo[k]fluoranthene	207-08-9	0.1	N.D.	1	0.5
Dibenzo[a,h]anthracene	53-70-3	0.1	N.D.	1	0.5

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel: +86/(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 8 of 25

Test Item(s)	CAS No.	MDL (mg/kg)	Test Result(s) (mg/kg)	Limited Value <sup>④</sup> (mg/kg)	
			6#	Category I	Category II
Benzo[a]pyrene	50-32-8	0.1	N.D.	1	0.5
Benzo[e]pyrene	192-97-2	0.1	N.D.	1	0.5
Benzo[a]anthracene	56-55-3	0.1	N.D.	1	0.5
Chrysene	218-01-9	0.1	N.D.	1	0.5
Benzo[b]fluoranthene	205-99-2	0.1	N.D.	1	0.5
Benzo[j]fluoranthene	205-82-3	0.1	N.D.	1	0.5
Benzo[k]fluoranthene	207-08-9	0.1	N.D.	1	0.5
Dibenzo[a,h]anthracene	53-70-3	0.1	N.D.	1	0.5

**Remark:** <sup>④</sup>The Limited value is based on EC Regulation 1907/2006,(EU) No 1272/2013 Amending PAHs of REACH Annex XVII(entry 50)

## LIMITS FOR PAHs :

Parameter	Category I	Category II
PAHs	Such articles include amongst other: 1. Sport equipment such as bicycles, golf clubs, racquets 2. House-hold utensils, trolleys, walking frames 3. tools for domestic use 4. clothing, footwear, gloves and sportwear 5. watch-straps, wrist-bands, masks, head-bands	Toys, including activity toys, and childcare articles

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel: +86/(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)



# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 9 of 25

## 5. Child care articles- Drinking equipment -Safety requirements and test methods- EN 14350:2020+A1:2023

Test Items	Test Result(s)
	7#
7 Construction and mechanical requirements and tests	
7.2 Decoration, inscription and decals	PASS
7.3 Visual and tactile examination	PASS
7.4 Small parts	PASS
7.5 Additional requirements for sealing discs	PASS
7.6 Requirements and tests for containers	PASS
7.6.1 Volumetric labelling requirements	PASS
7.6.2 Volumetric accuracy	PASS
7.6.3 Print adhesion of graduations	PASS
7.6.4 Thermal shock	PASS
7.7 Requirements and tests for drinking accessories	PASS
7.7.1 Tear resistance test	PASS
7.7.2 Push-pull valve	PASS
7.8 Protective covers	PASS
7.8.1 Size of detachable protective cover	PASS
7.8.2 Size of permanent protective cover	N/A
7.8.3 Security of permanent protective cover	N/A
7.9 Handles and clips	PASS
7.10 Finger traps	N/A
7.11 Protruding parts	PASS
7.11.1 Maximum length	PASS
7.11.2 Flexibility	PASS
7.11.3 Security/retention test of protruding parts	N/A
7.12 Cords or loops	N/A

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel: +86(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)



# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 10 of 25

Test Items	Test Result(s)
	7#
9 Consumer packaging	PASS

Test Items	Test Result(s)
	7#
10 Product information	PASS
10.1 General	PASS
10.2 Purchase information	PASS
10.3 Warnings	PASS
10.4 Instructions for use	PASS
10.5 Supply chain information for products that contain vulcanised rubber	N/A

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel: +86/(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 11 of 25

## 6. Migration of certain elements

### Test Method:

Extractable Chromium(VI): With reference to EN 71-3:2019+A1:2021, analysis was performed by IC-ICP-MS.

Extractable Chromium(III): With reference to EN 71-3:2019+A1:2021, calculated by subtracting the Chromium (VI) concentration from the total chromium concentration.

Other Elements: With reference to EN 71-3:2019+A1:2021, analysis was performed by ICP-MS.

Extractable Organic Tin: With reference to EN 71-3:2019+A1:2021, analysis was performed by GC-MS.

Test Item	MDL (mg/kg)	Test Result(s) (mg/kg)			Limited Value <sup>5</sup> (mg/kg)
		1#	2#	3#	
Antimony (Sb)	5	N.D.	N.D.	N.D.	120
Arsenic (As)	5	N.D.	N.D.	N.D.	10
Barium (Ba)	5	N.D.	N.D.	N.D.	4000
Cadmium (Cd)	1	N.D.	N.D.	N.D.	3.6
Lead (Pb)	1	N.D.	N.D.	N.D.	5.0
Chromium (Cr)	5	N.D.	N.D.	N.D.	---
Mercury (Hg)	5	N.D.	N.D.	N.D.	20
Selenium (Se)	5	N.D.	N.D.	N.D.	100
Aluminum (Al)	5	N.D.	N.D.	N.D.	6000
Boron (B)	5	N.D.	N.D.	N.D.	3200
Chromium (III)	5	N.D.	N.D.	N.D.	100
Chromium (VI)	0.002	N.D.	N.D.	N.D.	0.002
Cobalt (Co)	5	N.D.	N.D.	N.D.	28
Copper (Cu)	5	N.D.	N.D.	N.D.	1660
Manganese (Mn)	5	N.D.	N.D.	N.D.	600
Nickel (Ni)	5	N.D.	N.D.	N.D.	56
Strontium (Sr)	5	N.D.	N.D.	N.D.	12000
Tin (Sn)	5	N.D.	N.D.	N.D.	40000
Organic tin	1	N.D.	N.D.	N.D.	2.5
Zinc (Zn)	5	N.D.	N.D.	N.D.	10000

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel: +86(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 12 of 25

## 7. Volatile organic compounds content

**Test Method:** With reference to EN 14350:2020+A1:2023.

Test Item(s)	Test Condition	Test Result(s) (%)	Limited Value <sup>⑤</sup> (%)
		3#	
Volatile organic compounds content	200℃, 4h	0.329	0.5

## 8. Colour fastness

**Test Method:** With reference to EN 14350:2020+A1:2023.

Simulant used	Result(s)	Limited Value <sup>⑤</sup>
	2#	
3% Acetic acid (W/V) Aqueous Solution	No color release observed	No color release
Coconut fat	No color release observed	No color release

## 9. N-Nitrosamine and N-Nitrosatable Content

**Test Method:** Sample preparation with reference to EN 12868:2017, followed by analysis by GC/MS.

Test Items	MDL (mg/kg)	Test Result(s) (mg/kg)	Limited Value <sup>⑤</sup> (mg/kg)
		3#	
N-Nitrosamines	0.01	N.D.	0.01
N-Nitrosatable substances	0.1	N.D.	0.1

## 10. Extractable Formaldehyde Content

**Test Method:** Sample preparation in 3% Acetic acid at 70 °C for 2 hours with reference to EN 14350:2020; followed by analysis using UV-visible Spectrophotometer.

Test Item(s)	Unit	Result(s)	Limited Value <sup>⑤</sup>
		3#	
Extractable Formaldehyde	mg/L	<0.1	0.5

**Remark:** <sup>⑤</sup> The Limited value is based on EN 14350:2020+A1:2023.

\*\*\*\*\* To be continued \*\*\*\*\*

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 13 of 25

## 11. Overall Migration Test

**Test Method:** With reference to EN 1186-1:2002 for selection of conditions and test methods;  
EN 1186-3:2022 for overall migration in evaporable simulants

### Surface area(dm<sup>2</sup>)/Volume(ml):

1# 1/164	2# 1/100
3# 1/100	4# 1/100
5# 1/100	

Simulants	Unit	Test Condition	Result(s)			Maximum Permissible Limit	Conclusion*
			1#-1 <sup>st</sup>	1#-2 <sup>nd</sup>	1#-3 <sup>rd</sup>		
3% acetic acid	mg/kg	2 hours at 70°C	<10	<10	<10	60	PASS
50% ethanol	mg/kg	2 hours at 70°C	<10	<10	<10	60	PASS

Simulants	Unit	Test Condition	Result(s)			Maximum Permissible Limit	Conclusion*
			2#-1 <sup>st</sup>	2#-2 <sup>nd</sup>	2#-3 <sup>rd</sup>		
3% acetic acid	mg/kg	2 hours at 70°C	<10	<10	<10	60	PASS
50% ethanol	mg/kg	2 hours at 70°C	<10	<10	<10	60	PASS

Simulants	Unit	Test Condition	Result(s)			Maximum Permissible Limit	Conclusion*
			3#-1 <sup>st</sup>	3#-2 <sup>nd</sup>	3#-3 <sup>rd</sup>		
3% acetic acid	mg/kg	2 hours at 70°C	<10	<10	<10	60	PASS
50% ethanol	mg/kg	2 hours at 70°C	<10	<10	<10	60	PASS

Simulants	Unit	Test Condition	Result(s)			Maximum Permissible Limit	Conclusion*
			4#-1 <sup>st</sup>	4#-2 <sup>nd</sup>	4#-3 <sup>rd</sup>		
3% acetic acid	mg/kg	2 hours at 70°C	<10	<10	<10	60	PASS
50% ethanol	mg/kg	2 hours at 70°C	<10	<10	<10	60	PASS

Simulants	Unit	Test Condition	Result(s)			Maximum Permissible Limit	Conclusion*
			5#-1 <sup>st</sup>	5#-2 <sup>nd</sup>	5#-3 <sup>rd</sup>		
3% acetic acid	mg/kg	2 hours at 70°C	<10	<10	<10	60	PASS
50% ethanol	mg/kg	2 hours at 70°C	<10	<10	<10	60	PASS

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yin Zhu Road, High-new district, Suzhou, China 215129

Tel: +86(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 14 of 25

## 12. Soluble Heavy Metals

**Test Method:** Sample preparation in 3% Acetic acid at 70°C for 2 hours, followed by analysis using Inductively Coupled Plasma Optical Emission Spectrometer.

**Surface area(dm<sup>2</sup>)/Volume(ml):**

1# 1/164

2# 1/167

Test Item(s)	Unit	Result(s)			Maximum Permissible Limit
		1#-1 <sup>st</sup>	1#-2 <sup>nd</sup>	1#-3 <sup>rd</sup>	
Soluble Aluminium	mg/kg	<0.1	<0.1	<0.1	1
Soluble Antimony	mg/kg	<0.01	<0.01	<0.01	0.04
Soluble Arsenic	mg/kg	<0.01	<0.01	<0.01	0.01
Soluble Barium	mg/kg	<0.1	<0.1	<0.1	1
Soluble Cadmium	mg/kg	<0.001	<0.001	<0.001	0.002
Soluble Chromium	mg/kg	<0.01	<0.01	<0.01	0.01
Soluble Cobalt	mg/kg	<0.01	<0.01	<0.01	0.05
Soluble Copper	mg/kg	<0.1	<0.1	<0.1	5
Soluble Iron	mg/kg	<5	<5	<5	48
Soluble Lead	mg/kg	<0.01	<0.01	<0.01	0.01
Soluble Lithium	mg/kg	<0.01	<0.01	<0.01	0.6
Soluble Manganese	mg/kg	<0.01	<0.01	<0.01	0.6
Soluble Mercury	mg/kg	<0.01	<0.01	<0.01	0.01
Soluble Nickel	mg/kg	<0.01	<0.01	<0.01	0.02
Soluble Zinc	mg/kg	<0.1	<0.1	<0.1	5
Soluble Tungsten	mg/kg	<0.01	<0.01	<0.01	0.05
Soluble Europium	mg/kg	<0.01	<0.01	<0.01	Sum≤0.05
Soluble Gadolinium	mg/kg	<0.01	<0.01	<0.01	
Soluble Lanthanum	mg/kg	<0.01	<0.01	<0.01	
Soluble Terbium	mg/kg	<0.01	<0.01	<0.01	
Soluble Magnesium	mg/kg	<0.01	<0.01	<0.01	---
Soluble Calcium	mg/kg	<0.01	<0.01	<0.01	---
Soluble Potassium	mg/kg	<0.01	<0.01	<0.01	---
Soluble Sodium	mg/kg	<0.01	<0.01	<0.01	---
Soluble Ammonium	mg/kg	<0.01	<0.01	<0.01	---
<b>Conclusion*</b>	---	<b>PASS</b>			---

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yin Zhu Road, High-new district, Suzhou, China 215129

Tel: +86/(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 15 of 25

Test Item(s)	Unit	Result(s)			Maximum Permissible Limit
		2#-1 <sup>st</sup>	2#-2 <sup>nd</sup>	2#-3 <sup>rd</sup>	
Soluble Aluminium	mg/kg	<0.1	<0.1	<0.1	1
Soluble Antimony	mg/kg	<0.01	<0.01	<0.01	0.04
Soluble Arsenic	mg/kg	<0.01	<0.01	<0.01	0.01
Soluble Barium	mg/kg	<0.1	<0.1	<0.1	1
Soluble Cadmium	mg/kg	<0.001	<0.001	<0.001	0.002
Soluble Chromium	mg/kg	<0.01	<0.01	<0.01	0.01
Soluble Cobalt	mg/kg	<0.01	<0.01	<0.01	0.05
Soluble Copper	mg/kg	<0.1	<0.1	<0.1	5
Soluble Iron	mg/kg	<5	<5	<5	48
Soluble Lead	mg/kg	<0.01	<0.01	<0.01	0.01
Soluble Lithium	mg/kg	<0.01	<0.01	<0.01	0.6
Soluble Manganese	mg/kg	<0.01	<0.01	<0.01	0.6
Soluble Mercury	mg/kg	<0.01	<0.01	<0.01	0.01
Soluble Nickel	mg/kg	<0.01	<0.01	<0.01	0.02
Soluble Zinc	mg/kg	<0.1	<0.1	<0.1	5
Soluble Tungsten	mg/kg	<0.01	<0.01	<0.01	0.05
Soluble Europium	mg/kg	<0.01	<0.01	<0.01	Sum≤0.05
Soluble Gadolinium	mg/kg	<0.01	<0.01	<0.01	
Soluble Lanthanum	mg/kg	<0.01	<0.01	<0.01	
Soluble Terbium	mg/kg	<0.01	<0.01	<0.01	
Soluble Magnesium	mg/kg	<0.01	<0.01	<0.01	
Soluble Calcium	mg/kg	<0.01	<0.01	<0.01	---
Soluble Potassium	mg/kg	<0.01	<0.01	<0.01	---
Soluble Sodium	mg/kg	<0.01	<0.01	<0.01	---
Soluble Ammonium	mg/kg	<0.01	<0.01	<0.01	---
<b>Conclusion*</b>	---	<b>PASS</b>			---

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel: +86/(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 16 of 25

### 13. Specific Migration of Primary Aromatic Amine

**Test Method:** Sample preparation with reference to EN 13130-1:2004 with selection of simulant and condition, followed by analysis by LC/MS/MS & UV.

**Test Condition:** 3% Acetic acid, 2 hours at 70°C

**Surface area(dm<sup>2</sup>)/Volume(ml):**

1# 1/164

2# 1/167

Test Item(s)	Unit	Result(s)			Maximum Permissible Limit
		1#-1 <sup>st</sup>	1#-2 <sup>nd</sup>	1#-3 <sup>rd</sup>	
4-Aminobiphenyl	mg/kg	<0.001	<0.001	<0.001	0.002
Benzidine	mg/kg	<0.001	<0.001	<0.001	0.002
4-Chloro-o-toluidine	mg/kg	<0.001	<0.001	<0.001	0.002
2-Naphthylamine	mg/kg	<0.001	<0.001	<0.001	0.002
O-Aminoazotoluene	mg/kg	<0.001	<0.001	<0.001	0.002
5-nitro-o-toluidine	mg/kg	<0.001	<0.001	<0.001	0.002
4-Chloroaniline	mg/kg	<0.001	<0.001	<0.001	0.002
4-methoxy-m-phenylenediamine	mg/kg	<0.001	<0.001	<0.001	0.002
4,4'-methylenedianiline	mg/kg	<0.001	<0.001	<0.001	0.002
3,3'-Dichlorobenzidine	mg/kg	<0.001	<0.001	<0.001	0.002
3,3'-Dimethoxybenzidine	mg/kg	<0.001	<0.001	<0.001	0.002
3,3'-Dimethylbenzidine	mg/kg	<0.001	<0.001	<0.001	0.002
4,4'-methylenedi-o-toluidine	mg/kg	<0.001	<0.001	<0.001	0.002
P-Cresidine	mg/kg	<0.001	<0.001	<0.001	0.002
4,4'-Methylene-bis-(2-Chloro-aniline)	mg/kg	<0.001	<0.001	<0.001	0.002
4,4'-oxydianiline	mg/kg	<0.001	<0.001	<0.001	0.002
4,4'-Thiodianiline	mg/kg	<0.001	<0.001	<0.001	0.002
O-Toluidine	mg/kg	<0.001	<0.001	<0.001	0.002
4-methyl-m-phenylenediamine	mg/kg	<0.001	<0.001	<0.001	0.002
2,4,5-Trimethylaniline	mg/kg	<0.001	<0.001	<0.001	0.002
4-Aminoazobenzene	mg/kg	<0.001	<0.001	<0.001	0.002
O-Anisidine	mg/kg	<0.001	<0.001	<0.001	0.002
Other Primary Aromatic Amine	mg/kg	<0.01	<0.01	<0.01	Sum≤0.01
<b>Conclusion*</b>	---	<b>PASS</b>			---

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhong Road, High-new district, Suzhou, China 215129

Tel: +86(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)



# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 17 of 25

Test Item(s)	Unit	Result(s)			Maximum Permissible Limit
		2#-1 <sup>st</sup>	2#-2 <sup>nd</sup>	2#-3 <sup>rd</sup>	
4-Aminobiphenyl	mg/kg	<0.001	<0.001	<0.001	0.002
Benzidine	mg/kg	<0.001	<0.001	<0.001	0.002
4-Chloro-o-toluidine	mg/kg	<0.001	<0.001	<0.001	0.002
2-Naphthylamine	mg/kg	<0.001	<0.001	<0.001	0.002
O-Aminoazotoluene	mg/kg	<0.001	<0.001	<0.001	0.002
5-nitro-o-toluidine	mg/kg	<0.001	<0.001	<0.001	0.002
4-Chloroaniline	mg/kg	<0.001	<0.001	<0.001	0.002
4-methoxy-m-phenylenediamine	mg/kg	<0.001	<0.001	<0.001	0.002
4,4'-methylenedianiline	mg/kg	<0.001	<0.001	<0.001	0.002
3,3'-Dichlorobenzidine	mg/kg	<0.001	<0.001	<0.001	0.002
3,3'-Dimethoxybenzidine	mg/kg	<0.001	<0.001	<0.001	0.002
3,3'-Dimethylbenzidine	mg/kg	<0.001	<0.001	<0.001	0.002
4,4'-methylenedi-o-toluidine	mg/kg	<0.001	<0.001	<0.001	0.002
P-Cresidine	mg/kg	<0.001	<0.001	<0.001	0.002
4,4'-Methylene-bis-(2-Chloro-aniline)	mg/kg	<0.001	<0.001	<0.001	0.002
4,4'-oxydianiline	mg/kg	<0.001	<0.001	<0.001	0.002
4,4'-Thiodianiline	mg/kg	<0.001	<0.001	<0.001	0.002
O-Toluidine	mg/kg	<0.001	<0.001	<0.001	0.002
4-methyl-m-phenylenediamine	mg/kg	<0.001	<0.001	<0.001	0.002
2,4,5-Trimethylaniline	mg/kg	<0.001	<0.001	<0.001	0.002
4-Aminoazobenzene	mg/kg	<0.001	<0.001	<0.001	0.002
O-Anisidine	mg/kg	<0.001	<0.001	<0.001	0.002
Other Primary Aromatic Amine	mg/kg	<0.01	<0.01	<0.01	Sum≤0.01
<b>Conclusion*</b>	---	<b>PASS</b>			---

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhong Road, High-new district, Suzhou, China 215129

Tel: +86(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 18 of 25

## 14. Specific Migration of Bisphenol-A

**Test Method:** Sample preparation with reference to BS EN 13130-1:2004 with selection of simulants and condition, followed by analysis using High Performance Liquid Chromatography/ Mass Spectrometer (HPLC/MS).

### Surface area(dm<sup>2</sup>)/Volume(ml):

1# 1/164

3# 1/167

4# 1/167

5# 1/167

Test Item(s)	Unit	Result(s)			Maximum Permissible Limit
		1#-1 <sup>st</sup>	1#-2 <sup>nd</sup>	1#-3 <sup>rd</sup>	
Specific migration of Bisphenol-A in 3% acetic acid at 70°C, 2 hours	mg/kg	<0.01	<0.01	<0.01	0.05
<b>Conclusion*</b>	---	<b>PASS</b>			---

Test Item(s)	Unit	Result(s)			Maximum Permissible Limit
		3#-1 <sup>st</sup>	3#-2 <sup>nd</sup>	3#-3 <sup>rd</sup>	
Specific migration of Bisphenol-A in 3% acetic acid at 70°C, 2 hours	mg/kg	<0.01	<0.01	<0.01	0.05
<b>Conclusion*</b>	---	<b>PASS</b>			---

Test Item(s)	Unit	Result(s)			Maximum Permissible Limit
		4#-1 <sup>st</sup>	4#-2 <sup>nd</sup>	4#-3 <sup>rd</sup>	
Specific migration of Bisphenol-A in 3% acetic acid at 70°C, 2 hours	mg/kg	<0.01	<0.01	<0.01	0.05
<b>Conclusion*</b>	---	<b>PASS</b>			---

Test Item(s)	Unit	Result(s)			Maximum Permissible Limit
		5#-1 <sup>st</sup>	5#-2 <sup>nd</sup>	5#-3 <sup>rd</sup>	
Specific migration of Bisphenol-A in 3% acetic acid at 70°C, 2 hours	mg/kg	<0.01	<0.01	<0.01	0.05
<b>Conclusion*</b>	---	<b>PASS</b>			---

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yin Zhu Road, High-new district, Suzhou, China 215129

Tel: +86(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 19 of 25

## 15. Bisphenol-A (BPA) Content

**Test Method:** With reference to EPA3550C-2007, Analysis was performed by LC-MS.

Test Item(s)	Unit	MDL	Result(s)		Limit
			1#	2#	
Bisphenol-A (BPA)	mg/kg	0.1	N.D.	N.D.	Absent

Test Item(s)	Unit	MDL	Result(s)		Limit
			3#	4#	
Bisphenol-A (BPA)	mg/kg	0.1	N.D.	N.D.	Absent

Test Item(s)	Unit	MDL	Result(s)	Limit
			5#	
Bisphenol-A (BPA)	mg/kg	0.1	N.D.	Absent

## 16. Volatile Organic Matter (VOM)

**Test Method:** With reference to French Arrêté du Novembre 1992 Annex III.

**Test Condition:** 200°C, 4 hours

Test Item(s)	Unit	Result(s)		Maximum Permissible Limit
		3#	4#	
Volatile organic matter (VOM)	% w/w	0.222	0.172	0.5

Test Item(s)	Unit	Result(s)	Maximum Permissible Limit
		5#	
Volatile organic matter (VOM)	% w/w	<0.05	0.5

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yin Zhu Road, High-new district, Suzhou, China 215129

Tel: +86/(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 20 of 25

## 17. Peroxide Value

**Test Method:** With reference to European pharmacopoeia, 2005 Appendix X F. Peroxide Value method A.

Test Item(s)	Result(s)		Maximum Permissible Limit
	3#	4#	
Peroxide Value	Absent	Absent	Absent

Test Item(s)	Result(s)	Maximum Permissible Limit
	5#	
Peroxide Value	Absent	Absent

## 18. Specific Migration of Tin

**Test Method:** Sample preparation in 3% Acetic acid at 70°C for 2 hours, followed by analysis using Inductively Coupled Plasma Optical Emission Spectrometer.

**Surface area(dm<sup>2</sup>)/Volume(ml):**

3# 1/167

4# 1/167

5# 1/167

Test Item(s)	Unit	Result(s)			Maximum Permissible Limit
		3#-1 <sup>st</sup>	3#-2 <sup>nd</sup>	3#-3 <sup>rd</sup>	
Specific migration of Tin	mg/kg	<0.01	<0.01	<0.01	0.1
<b>Conclusion*</b>	---	<b>PASS</b>			---

Test Item(s)	Unit	Result(s)			Maximum Permissible Limit
		4#-1 <sup>st</sup>	4#-2 <sup>nd</sup>	4#-3 <sup>rd</sup>	
Specific migration of Tin	mg/kg	<0.01	<0.01	<0.01	0.1
<b>Conclusion*</b>	---	<b>PASS</b>			---

Test Item(s)	Unit	Result(s)			Maximum Permissible Limit
		5#-1 <sup>st</sup>	5#-2 <sup>nd</sup>	5#-3 <sup>rd</sup>	
Specific migration of Tin	mg/kg	<0.01	<0.01	<0.01	0.1
<b>Conclusion*</b>	---	<b>PASS</b>			---

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yin Zhu Road, High-new district, Suzhou, China 215129

Tel: +86(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)

# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 21 of 25

**Remark:** \*According to Regulation (EU) No 10/2011 and its amendment (EU) 2020/1245, for repeated use materials and articles:

- 1) The applicable overall migration test shall be carried out three times on a single sample. The overall migration in the second test shall be lower than in the first test, and the overall migration in the third test shall be lower than in the second test. Compliance with the overall migration limit shall be verified on the basis of the level of the overall migration found in the third test.
- 2) Specific migration test(s) shall be carried out three times on a single sample. Compliance shall then be verified on the basis of the level of the migration found in the third test and on the basis of the stability of the material or article from the first to the third migration test. The stability of the material shall be considered insufficient if migration is observed above the level of detection in any of the three migration tests, and increases from the first migration test to the third migration test. In case of insufficient stability, compliance of the material shall not be established even in case the specific migration limit is not exceeded in any of the three tests. Irrespective of the above rules, a material or article shall never be considered to comply with the Regulation if in the first test a substance that is prohibited from migrating or from being released in detectable quantities.

- Note:**
- 1) MDL = Method Detection Limit.
  - 2) N.D. = Not detected, less than MDL.
  - 3) “---” = Not Regulated.
  - 4) % = Percentage by weight.

## Test Part Description:

- 1# Transparent plastic cup body(Tritan)
- 2# Green plastic cover(PP)
- 3# Translucent silicone ring
- 4# Transparent silicone straw
- 5# Transparent silicone nozzle
- 6# Multicolor coating
- 7# Toddler's sippy cup tritan

\*\*\*\*\* To be continued \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel: +86/(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)


Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)


### SAMPLE PHOTOS




1#




2#




3#



4#



5#




6#

**TEST REPORT**

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 23 of 25



7#



7#

	<p>MOB / MO2330 PO BOX 644 6710 BP(NL) PO41-114031 Made in China Age:6 months+</p>
	<p>EN14350:2020+A1:2023</p>

7#

<p><b>USER MANUAL</b></p>			
<p>正面</p>		<p>背面</p>	
<p>1. 使用前请仔细阅读本用户手册，并妥善保管。如有任何疑问，请联系我们的客户服务中心。</p> <p>2. 本产品适用于6个月以上的婴幼儿使用。请勿让婴幼儿长时间使用，以免导致脱水或电解质紊乱。</p> <p>3. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>4. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>5. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>6. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>7. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>8. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>9. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>10. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p>	<p>1. 使用前请仔细阅读本用户手册，并妥善保管。如有任何疑问，请联系我们的客户服务中心。</p> <p>2. 本产品适用于6个月以上的婴幼儿使用。请勿让婴幼儿长时间使用，以免导致脱水或电解质紊乱。</p> <p>3. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>4. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>5. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>6. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>7. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>8. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>9. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>10. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p>	<p>1. 使用前请仔细阅读本用户手册，并妥善保管。如有任何疑问，请联系我们的客户服务中心。</p> <p>2. 本产品适用于6个月以上的婴幼儿使用。请勿让婴幼儿长时间使用，以免导致脱水或电解质紊乱。</p> <p>3. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>4. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>5. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>6. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>7. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>8. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>9. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>10. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p>	<p>1. 使用前请仔细阅读本用户手册，并妥善保管。如有任何疑问，请联系我们的客户服务中心。</p> <p>2. 本产品适用于6个月以上的婴幼儿使用。请勿让婴幼儿长时间使用，以免导致脱水或电解质紊乱。</p> <p>3. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>4. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>5. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>6. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>7. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>8. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>9. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p> <p>10. 请勿让婴幼儿长时间使用本产品，以免导致脱水或电解质紊乱。</p>

7#

**REFERENCE PHOTOS**



\*\*\*\*\* END OF REPORT \*\*\*\*\*

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yin Zhu Road, High-new district, Suzhou, China 215129

Tel: +86/(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)



# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May, 22, 2024

Page No.: 24 of 25

## GENERAL CONDITIONS OF SERVICES

STQ Testing Services Co.,Ltd. (hereinafter "STQ"), The testing or examining under the request of the customer should obey terms as follow, according to regulation of "Contract Law of the People's Republic of China" on processing and undertaking contract, our company have legal right of termination without any reason and have the right to accept or refuse testing or examining request:

1. STQ only acts for the person or body originating the instructions (the "Clients"). No other party is entitled to give instructions, particularly on the scope of testing or delivery of report or certificate, unless authorized by the Clients.
2. The delivery and return fee of the samples which need to do testing at STQ should be paid by the client. STQ will not bear the responsibility for the testing error that is caused by transporting, packaging and labelling.
3. Sample recycling: when the testing or examining is finished, the customer should recycle the sample. Within 30 days after issuing of testing report, if the customer could not recycle the sample or send notification of sample recycling in written (for example, if the sample belongs to consumables, toxic drugs, dangerous goods and other items that are not suitable for long-term storage, such as semi-finished products and fragile samples such as liquids and powders, the retention period will be shortened to 7 days). After the retention period, STQ has the right to dispose of the sample arbitrarily without paying compensation or compensation to the customer and take no responsibility for the consequences that damages the customer's trade secrets and intellectual property rights due to the loss of the sample.
4. The Clients shall always comply with the following before or during STQ providing its services:
  - a) provide sample(s) and relevant data, at the same time, guarantee the consistence of the sample(s)' name they declared with the sample(s) or the goods provided. Otherwise, STQ will not bear any relevant responsibilities;
  - b) giving timely instructions and adequate information to enable STQ to perform the services effectively;
  - c) supply, when requested by STQ, any equipment and personnel for the performance of the services;
  - d) take all necessary steps to eliminate or remedy any obstruction in the performance of the services;
  - e) inform STQ in advance of any hazards or dangers, actual or potential, associated with any order of samples or testing;
  - f) provide all necessary access for STQ's representative to enable the required services to be performed effectively;
  - g) ensure all essential steps are taken for safety of working conditions, sites and installations during the performance of services;
  - h) fully discharge all its liabilities under any contract like sales contract with a third party, whether or not a report or certificate has been issued by STQ, failing which STQ shall be under no obligation to the Clients.
5. Subject to STQ's accepting the Client's instructions, STQ will issue reports or certificates which reflect statements of opinion made with due care within the scope of instructions but STQ is not obliged to report upon any facts outside the instructions, if there were any dissidence about the report or certificate, the Client should provide the written declaration to STQ within 15 days after the date receiving the report or certificate, otherwise, STQ will not hear the case after the date limit.
6. STQ is irrevocably authorized by the Clients to deliver at its discretion the report or the certificate to any third party when instructed by the Clients or where it implicitly follows from circumstances, trade custom, usage or practice as determined by STQ.
7. A test report will be issued in confidence to the Clients and it will be strictly treated as such by STQ. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of STQ. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by STQ, to his customer, supplier or other persons directly concerned. STQ will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the report unless required by the relevant governmental authorities, laws or court orders.
8. Applicants wishing to use STQ's reports in court proceedings or arbitration shall inform STQ to that effect prior to submitting the sample for testing.
9. The report will refer only to the sample tested and will not apply to the bulk, unless the sampling has been carried out by STQ and is stated as such in the Report. Also, the report is only for reference.
10. Any documents containing engagements between the Clients and third parties like contracts of sale, letters of credit, bills of lading, etc. are regarded as information for STQ only and do not affect the scope of the services or the obligations accepted by STQ.
11. If the Clients do not specify the methods/standards to be applied, STQ will choose the appropriate ones and further information regarding the methods can be obtained by direct contact with STQ, for the in-house method, STQ will only provide the summary.
12. No liability shall be incurred by and no claim shall be made against STQ or its servants, agents, employees or independent contractors in respect of any loss or damage to any such materials, equipment and property occurring whilst at STQ or any work places in which the testing is carried out, or in the course of transit to or from STQ or the said work places, whether or not resulting from any acts, neglect or default on the part of any such servants, agents, employees or independent contractors of STQ.
13. STQ will not be liable, or accept responsibility for any loss or damage howsoever arising from the use of information contained in any of its reports or in any communication whatsoever about its said tests or investigations.
14. Except for term 11 and term 12, if the test sample is damaged due to the negligence of STQ, the total compensation for loss and damage to the sample or loss to the customer shall not exceed twice of the test service fee.
15. In the event of STQ prevented by any cause outside STQ's control from performing any service for which an order has been given or an agreement made, the Clients shall pay to STQ:
  - a) the amount of all abortive expenditure actually made or incurred;

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yin Zhu Road, High-new district, Suzhou, China 215129

Tel: +86/(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)





# TEST REPORT

Reference No. : SZ2024041281-1E

Date : May. 22, 2024

Page No.: 25 of 25

- b) a proportion of the agreed fee or commission equal to the proportion (if any) of the service actually carried out by STQ, and STQ shall be relieved of all responsibility whatsoever for the partial or total non-performance of the required service.
16. STQ shall be discharged from all liabilities for all claims for loss, damage or expense unless suit is brought within one calendar year after the date of the performance by STQ of the service relating to the claim or in the event of any alleged non-performance within one year of the date when such service should have been completed.
  17. The Clients acknowledge that STQ does not, either by entering into a contract or by performing service, assume or undertake to discharge any duty of the Clients to any other persons. STQ is neither an insurer nor a guarantor and disclaims all liability in such capacity.
  18. The Clients shall hold harmless and indemnify STQ and its officers, employees, agents or independent contractors against all claims made by any third party for loss, damage or expense of whatsoever nature including reasonable legal expenses relating to the performance or non-performance of any services to the extent that the aggregate of any such claims relating to any one service exceed the limits mentioned in Clause 13.
  19. Any unauthorized alteration, forgery or falsification of the content or appearance of the report/certificate is unlawful and offenders may be prosecuted to the fullest extent of the law; in the event of improper use of the report, STQ reserves the right to withdraw it, and to adopt any other measures which may be appropriate.
  20. Samples are deposited with and accepted by STQ on the basis that either they are insured by the Clients or the Clients assumes entire responsibility for loss through fire, theft, burglary or for damages arising in the course of analysis or handling, without recourse whatsoever to STQ or its servants, agent, employees or independent contractors.
  21. If the requirements of the Clients require the analysis of samples by the Clients' or any third party's laboratory, STQ will only convey the result of the analysis without responsibility for its accuracy. If STQ is only able to witness an analysis by the Clients' or any third Party's laboratory STQ will only confirm that the correct sample has been analyzed without responsibility for the accuracy of any analysis or results.
  22. In the event of any unforeseen additional time or costs being incurred in the course of carrying out any of its services, STQ shall be entitled to charge the Clients additional fees to reflect the additional time and costs incurred.
  23. All rights (including but not limited to copyright) in any reports, certificates or other materials produced by STQ in the course of providing its services shall remain vested in STQ.
  24. Unless otherwise agreed in written, payment should be arranged within 10 days after the invoice date or the debit note date. If the payment is overdue, the overdue penalty shall be calculated at 1‰ per day of the unpaid part till the actual payment date. All expenses, costs and losses incurred by STQ as a result of collecting or claiming the fees owed shall be borne by the customer, including but not limited to attorney fees, litigation fees, preservation fees, preservation guarantee fees, travel expenses, etc.
  25. Test results may be transmitted by electronic means at the Client's request. However, it should be noted that electronic transmission cannot guarantee the information contained will not be lost, delayed or intercepted by third party. STQ is not liable for any disclosure, error or omission in the content of such messages as a result of electronic transmission.
  26. If necessary, STQ may subcontract part of or all tests to competent subcontractors. If no objection is raised at the time of the Clients submitting the application, STQ shall assume the Client's approval.
  27. This report/certificate does not relieve sellers/suppliers from their contractual responsibility with regards to the quality/quantity of this delivery nor does it prejudice the Client's right to claim towards sellers/suppliers for compensation for any apparent and/or hidden defects not detected during STQ's random inspection or testing or audit.
  28. The testing data and result(s) in this report is(are) just for scientific research, education, internal quality control and product development etc.
  29. STQ reserves the right to include Special Conditions in addition to the foregoing General Conditions if warranted by the particular circumstances of the required test or investigation [this clause is only effective when the other party has been informed].
  30. The foregoing General Conditions shall in all respects be governed, construed, interpreted and operated in accordance with the relevant Chinese laws and regulations. Unless otherwise agreed, the arbitration shall take place in P. R. C
  31. These General Condition have been drafted in Chinese and may be translated into other languages. In the event of any discrepancy, the Chinese version shall prevail.
  32. In general sample will be stored for 30 days. But for liquid, powder, etc semi-product & fragile product, it will be stored for 15 days after the report is issued.

STQ Testing Services Co., Ltd.

Add.: Building 1, 15 Yinzhu Road, High-new district, Suzhou, China 215129

Tel: +86/(0)512 67991866

Web: [www.stq-cert.com](http://www.stq-cert.com)

Technical service: [TS@stq-cert.com](mailto:TS@stq-cert.com)

Customer service: [CS@stq-cert.com](mailto:CS@stq-cert.com)

Report checking: [Report@stq-cert.com](mailto:Report@stq-cert.com)

Complaint: [QA@stq-cert.com](mailto:QA@stq-cert.com)