



# **TEST REPORT**

Report No.....: WTF22F04079772F

Applicant..... : Mid Ocean Brands B.V.

Wan, Kowloon, Hong Kong

**Manufacturer** ..... 115649

Sample Name .....: Sublimation mug with spoon

Model No. ..... MO6581

Test Requested .....: In accordance with Council of Europe Resolution

84/500/EC (2005/31/EC) and Regulation (EC) No

1935/2004.

Test Conclusion .....: Pass (Please refer to next pages for details)

Date of Receipt sample ...... : 2022-04-25

**Testing period** ...... : 2022-04-25 to 2022-04-29

**Date of Issue** ..... 2022-04-29

Test Result..... : Refer to next page (s)

# Prepared By:

## Waltek Testing Group (Foshan) Co., Ltd.

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Signed for and on behalf of Waltek Testing Group (Foshan) Co., Ltd.

Jessise Liu

Jessise.Liu



Report No.: WTF22F04079772F

# **Test Results:**

#### **Extractable Lead and Cadmium Content**

	TOTAL CONTROLL			
Test Items	Result (mg/L)	1.00 (mg/l)	Limit (ma/L)	
restitems	No.1	LOQ (mg/L) Limit (mg/		
Extractable Lead	mer an ND and	0.1	4.0	
Extractable Cadmium	ALTER MITTEND NITE WALL	0.01	0.3	

the state of the state of	Result (mg/dm²)	100 (=== (d== 2)	Limit (mg/dm²)
Test Items	No.2	LOQ (mg/dm <sup>2</sup> )	
Extractable Lead	My MD		0.8
Extractable Cadmium	INTERNAL ND WALL WAS	0.01	0.07

## Note:

- 1. Test method: With reference to BS EN 1388-1:1996 and BS EN 1388-2:1996, sample preparation in 4% acetic acid at 22±2°C for 24 hours, analysis was performed by ICP-MS.
- 2. "mg/L" = milligram per litre
- 3. "mg/dm<sup>2</sup>" = milligram per square decimetre
- 4. LOQ = Limit of quantitation
- 5. ND = Not Detected, less than limit of quantitation
- 6. The specification was quoted from 84/500/EC (2005/31/EC).






Report No.: WTF22F04079772F

# Sample Photo:





No.	Photo of testing part	Parts Description	Client Claimed Material
L MALE		TEX WIFEX WIFEX	TEX MUTER WATER WIT
MILITER M		White ceramic	Ceramic
		MALIER MALIER MALIER	White white while y
	7 3 4 5 6 7 8 9 10 11 12 13 11 15 16 17 18 19 20 21 22	23 28 TEX STEEL STEEL	LIFEX WHITEK WHITEK W





Report No.: WTF22F04079772F

No.	Photo of testing part	Parts Description	Client Claimed Materia
White S.		et mitel whitel wat	CA MULTER MULTER MULTER
		TEX STEEL STEEL	UNLIER WHITER WHITER
2	To Control of the Con	White ceramic	Ceramic
	OT O	nife while whi.	her he he h
		the the this is	WELL WILL MALL WALL

#### Remarks:

- 1. The results shown in this test report refer only to the sample(s) tested;
- 2. This test report cannot be reproduced, except in full, without prior written permission of the company;
- 3. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver;
- 4. The Applicant name and Address, the sample(s) and sample information was/were provided by the applicant who should be responsible for the authenticity which Waltek hasn't verified;
- 5. If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.

===== End of Report ======

