

Test Report

Report No. : AGC05443240310-001

SAMPLE NAME : Foldable knife with bamboo handle and PU rope

MODEL NAME : MO6623

APPLICANT: MID OCEAN BRANDS B.V

STANDARD(S) : Please refer to the following page(s).

DATE OF ISSUE : Mar. 14, 2024

Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd.





MID OCEAN BRANDS B.V

Address 7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong. Test Site 6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community, Hangcheng Street,

Bao'an District, Shenzhen, Guangdong, China

Report on the submitted sample(s) said to be:

Sample Name Foldable knife with bamboo handle and PU rope

Model MO6623 Vendor code 115205 Country of Origin **CHINA** Country of Destination **EUROPE** Sample Received Date Mar. 07, 2024

Testing Period Mar. 07, 2024 to Mar. 14, 2024

Test Requested Selected test(s) as requested by client.

Test Requested: Conclusion

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 63

Pass - Lead(Pb) Content

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 23

-Cadmium(Cd) Content

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 51&52

Pass - Phthalates Content

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50

- Polycyclic-aromatic Hydrocarbons (PAHs) Content

Regulation (EU) 2019/1021 on persistent organic pollutants (POPs)

- Pentachlorophenol (PCP) Content

- Formaldehyde Release Pass

Regulation 1935/2004/EC and Technical Guide on Metals and alloys used in food contact materials

of Council of Europe Resolution CM/Res(2013)9

- Specific migration of Heavy metal

Approved by: Leon

Report No.: AGC05443240310-001

Pass

Pass

Pass

Pass

Suhongliang, Leon

Technical Director



Report Revise Record


Report No.: AGC05443240310-0	01
------------------------------	----

Report Version	Issued Date	Valid Version	Notes
/	Mar. 14, 2024	Valid	Initial release



Report No.: AGC05443240310-001

The photo of the sample



The photo of AGC05443240310-001 is for use only with the original report.

Test Point Description

Test point	Test point description
1-1	Bamboo handle
1-2	Brown PU rope
1-3	Metal hinge
1-4	Metal knife



Report No.: AGC05443240310-001

 $Note: N.D. = Not \ Detected \ (less \ than \ method \ detection \ limit), \ MDL = Method \ Detection \ Limit, \ 1mg/kg = 0.0001\%$

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 63

- Lead(Pb) Content

Test Methods and Equipment: IEC 62321-5:2013; ICP-OES

Tost Itam(s)	Unit Limit		MDL	Test Result(s)	
Test Item(s)	Omi	Lillit	MIDL	1-1	1-2
Lead(Pb)	mg/kg	500	10	N.D.	N.D.
Conclusion				Conformity	Conformity

Tost Itom(s)	Unit Limit	MDI	Test Result(s)		
Test Item(s)	Unit	Limit	MDL	1-3	1-4
Lead(Pb)	mg/kg	500	10	N.D.	N.D.
Conclusion				Conformity	Conformity

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 23

-Cadmium(Cd) Content

Test Methods and Equipment: IEC 62321-5:2013; ICP-OES

Test Item(s)	Unit	Limit	MDI	Test Result(s)
Test tiem(s)	Unit	Lillit	MDL	1-2
Cadmium(Cd)	mg/kg	100	10	N.D.
Conclusion				Conformity



Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 51&52

- Phthalates Content

Test Methods and Equipment: IEC 62321-8:2017; GC-MS

Test Item(s)	Unit	Limit	MDL	Test Result(s) 1-2
Diisobutyl phthalate (DIBP) CAS:84-69-5	%	0.1	0.005	N.D.
Dibutyl phthalate (DBP) CAS:84-74-2	%	0.1	0.005	N.D.
Butylbenzyl phthalate (BBP) CAS:85-68-7	%	0.1	0.005	N.D.
Di-(2-ethylhexyl) Phthalate (DEHP) CAS:117-81-7	%	0.1	0.005	N.D.
Di-n-octyl phthalate (DNOP) CAS:117-84-0	%	/	0.005	N.D.
Di-isononyl phthalate (DINP) CAS:28553-12-0, 68515-48-0	%	/	0.005	N.D.
Di-isodecyl phthalate(DIDP) CAS:26761-40-0, 68515-49-1	%	/	0.005	N.D.
Sum of DIBP +DBP+BBP+DEHP	%	0.1	/	N.D.
Sum of DNOP+DINP+DIDP	%	0.1	/	N.D.
Со	Conformity			

Limit requirements of Phthalates

Toys and childcare articles	Each of DEHP, DBP, BBP, DIBP is less than 0.1% or the sum of DEHP+DBP+BBP+DIBP is less than 0.1%
Toys and childcare articles which can be placed in the mouth by children	The sum of DINP+DIDP+DNOP is less than 0.1%

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Report No.: AGC05443240310-001



Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50

- Polycyclic-aromatic Hydrocarbons (PAHs) Content

Test Methods and Equipment: Afps GS 2019:01 PAK; GC-MS

Test Item(s)	Unit	Limit	MDL	Test Result(s) 1-2
Benzo[a]pyrene(BaP)	mg/kg	1	0.1	N.D.
Benzo[e]pyrene(BeP)	mg/kg	1	0.1	N.D.
Benzo[a]anthracene(BaA)	mg/kg	1	0.1	N.D.
Benzo[b]fluoranthene(BbF)	mg/kg	1	0.1	N.D.
Benzo[j]fluoranthene(BjFA)	mg/kg	1	0.1	N.D.
Benzo[k]fluoranthene(BkF)	mg/kg	1	0.1	N.D.
Chrysene(CHR)	mg/kg	1	0.1	N.D.
Dibenzo[a,h]anthracene(DBA)	mg/kg	1	0.1	N.D.
Co	onclusion			Conformity

Limit requirements of Polycyclic-aromatic Hydrocarbons (PAHs) (Unit: mg/kg)

Items	CAS No.	Extender oils or used for the production of tyres or parts of tyres	Any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity	Toys, including activity toys, and childcare articles, any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity
Benzo[a]pyrene(BaP)	50-32-8	≤ 1	≤1	≤ 0.5
Benzo[e]pyrene(BeP)	192-97-2	/	≤ 1	≤ 0.5
Benzo[a]anthracene(BaA)	56-55-3	/	≤1	≤ 0.5
Benzo[b]fluoranthene(BbF)	205-99-2	/	≤1	≤ 0.5
Benzo[j]fluoranthene(BjFA)	205-82-3	/	≤ 1	≤ 0.5
Benzo[k]fluoranthene(BkF)	207-08-9	/	≤1	≤ 0.5
Chrysene(CHR)	218-01-9	/	≤ 1	≤ 0.5
Dibenzo[a,h]anthracene(DBA)	53-70-3	/	≤ 1	≤ 0.5
Sum of BaP+ BeP+ BaA+ BbF+ BjFA+ BkF+ CHR+ DBA	/	≤ 10	/	/

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Report No.: AGC05443240310-001



Regulation (EU) 2019/1021 on persistent organic pollutants (POPs)

- Pentachlorophenol (PCP) Content

Test Methods and Equipment: EPA 3550C:2007 & EPA 8270E:2018; GC-MS


Test Itam(s)	T Lait	T ::4	MDI	Test Result(s)
Test Item(s)	Unit Limit MI		MDL	1-1
Pentachlorophenol (PCP)	mg/kg	5	5	N.D.
Co	Conformity			

Report No.: AGC05443240310-001

- Formaldehyde Release

Test Methods and Equipment: EN 717-3:1996; UV-Vis


Tost Itom(s)	Unit	Client's	MDI	Test Result(s)
Test Item(s)	Unit	limit	MDL	1-1
Formaldehyde Release	mg/kg	80	1	4
Co	nclusion			Conformity






- Specific migration of Heavy metal

Test Item(s)	Test condition/ Equipment	MDL (mg/kg)	Test Result(s) (mg/kg) 1-4 1st + 2nd extractives	Limit (mg/kg)
Copper (Cu)		0.1	N.D.	28
Iron (Fe)		0.1	N.D.	280
Tin (Sn)		0.1	N.D.	700
Chromium (Cr)		0.01	N.D.	1.75
Manganese (Mn)		0.1	N.D.	12.6
Zinc (Zn)		0.1	N.D.	35
Aluminium (Al)		0.1	0.270	35
Lithium (Li)		0.01	N.D.	0.336
Beryllium (Be)		0.005	N.D.	0.07
Vanadium (V)		0.005	N.D.	0.07
Nickel (Ni)	0.5% Citric acid 70°C, 2h, ICP-OES	0.01	N.D.	0.98
Cobalt (Co)		0.01	N.D.	0.14
Arsenic (As)		0.002	N.D.	0.014
Molybdenum(Mo)		0.01	N.D.	0.84
Silver (Ag)		0.01	0.042	0.56
Cadmium (Cd)		0.002	N.D.	0.035
Antimony (Sb)		0.01	N.D.	0.28
Mercury (Hg)		0.002	N.D.	0.021
Thallium (Tl)		0.0001	N.D.	0.0007
Lead (Pb)		0.01	N.D.	0.07
Conclusion		/	Conformity	/
Magnesium (Mg)		0.01	0.019	/
Titanium (Ti)		0.01	N.D.	/






Test Item(s)	Test condition/ Equipment	MDL (mg/kg)	Test Result(s) (mg/kg) 1-4 3rd extractives	Limit (mg/kg)
Barium (Ba)		0.1	N.D.	1.2
Copper (Cu)	-	0.1	N.D.	4
Iron (Fe)		0.1	N.D.	40
Tin (Sn)		0.1	N.D.	100
Chromium (Cr)	_	0.01	N.D.	0.25
. ,		0.01	N.D.	1.8
Manganese (Mn)				
Zinc (Zn)		0.1	N.D.	5
Aluminium (Al)		0.1	N.D.	5
Lithium (Li)		0.01	N.D.	0.048
Beryllium (Be)		0.005	N.D.	0.01
Vanadium (V)		0.005	N.D.	0.01
Nickel (Ni)	0.5% Citric acid 70°C, 2h, ICP-OES	0.01	N.D.	0.14
Cobalt (Co)		0.01	N.D.	0.02
Arsenic (As)		0.002	N.D.	0.002
Molybdenum(Mo)		0.01	N.D.	0.12
Silver (Ag)		0.01	0.019	0.08
Cadmium (Cd)		0.002	N.D.	0.005
Antimony (Sb)		0.01	N.D.	0.04
Mercury (Hg)		0.002	N.D.	0.003
Thallium (Tl)		0.0001	N.D.	0.0001
Lead (Pb)		0.01	N.D.	0.01
Conclusion		/	Conformity	/
Magnesium (Mg)		0.01	N.D.	/
Titanium (Ti)		0.01	N.D.	/







Test Flow Chart of Heavy Metal Content




Test Flow Chart of Phthalates









Test Flow Chart of Polycyclic-aromatic Hydrocarbons (PAHs)









Test Flow Chart of Pentachlorophenol (PCP)







Test Flow Chart of Formaldehyde Release





Report No.: AGC05443240310-001

Conditions of Issuance of Test Reports

- 1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the "Company") solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the "Clients").
- 2. Any report issued by Company as a result of this application for testing services (the "Report") shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.
- 3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.
- 4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.
- 5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.
- 6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations. 7. Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.
- 8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.
- 9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

*** End of Report ***