



中国认可  
国际互认  
检测  
TESTING  
CNAS L6478



# TEST REPORT

**Reference No.** ..... : WTF20F10074293X1F

**Applicant** ..... : Mid Ocean Brands B.V.

**Address** ..... : 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong

**Manufacturer** ..... : 115649

**Sample Name** ..... : Mug with spoon

**Model No.** ..... : MO7344, MO8422

**Test Requested** ..... : In accordance with Council of Europe Resolution 84/500/EC (2005/31/EC) and Regulation (EC) No 1935/2004.

**Test Conclusion** ..... : **Pass** (Please refer to next pages for details)

**Date of Receipt sample** .... : 2020-09-15 & 2020-10-14

**Date of Test** ..... : 2020-09-15 to 2020-09-21 ~ 2020-10-14 to 2020-10-20

**Date of Issue** ..... : 2020-12-16

**Test Result** ..... : Please refer to next page (s)

**Note** ..... : As per client's requirement, the results from No.1 to No.9 were quoted from Report No. WTF20F09066795F  
This report is based on Waltek test report WTF20F10074293F for revising, and replaced report WTF20F10074293F.

**Remarks:**

The results shown in this test report refer only to the sample(s) tested; this test report cannot be reproduced, except in full, without prior written permission of the company. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver.  
If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.

**Prepared By:**

**Waltek Testing Group (Foshan) Co., Ltd.**

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City,  
Chencun, Shunde District, Foshan, Guangdong, China

Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Compiled by:

*Abby Zhou*

Abby.Zhou / Project Engineer

Approved by:

*Dino Zhang*

Dino.Zhang / Technical Manager

**Test Results:****Extractable Lead and Cadmium Content**

Test Items	Result (mg/L)			LOQ (mg/L)	Limit (mg/L)
	No.1	No.2	No.3		
Extractable Lead	ND	ND	ND	0.1	4.0
Extractable Cadmium	ND	ND	ND	0.01	0.3

Test Items	Result (mg/L)			LOQ (mg/L)	Limit (mg/L)
	No.4	No.5	No.6		
Extractable Lead	ND	ND	ND	0.1	4.0
Extractable Cadmium	ND	ND	ND	0.01	0.3

Test Items	Result (mg/dm <sup>2</sup> )	LOQ (mg/dm <sup>2</sup> )	Limit (mg/dm <sup>2</sup> )
	No.7		
Extractable Lead	ND	0.1	0.8
Extractable Cadmium	ND	0.01	0.07

Test Items	Result (mg/L)			LOQ (mg/L)	Limit (mg/L)
	No.8	No.9	No.10		
Extractable Lead	ND	ND	ND	0.1	4.0
Extractable Cadmium	ND	ND	ND	0.01	0.3

**Note:**

1. Test method: With reference to BS EN 1388-1: 1996 and BS EN 1388-2: 1996, sample preparation in 4% acetic acid at 22±2°C for 24 hours, analysis was performed by ICP-OES.
2. "mg/L" = milligram per litre
3. "mg/dm<sup>2</sup>" = milligram per square decimetre
4. LOQ = Limit of quantitation
5. ND = Not Detected, less than limit of quantitation
6. The specification was quoted from 84/500/EC (2005/31/EC).



**Sample Photo:**









Photograph of parts tested:

No.	Photo of testing part	Parts Description	Client Claimed Material
1		Blue ceramic	Ceramic
2		Blue ceramic	Ceramic



No.	Photo of testing part	Parts Description	Client Claimed Material
3		Green ceramic	Ceramic
4		Green ceramic	Ceramic
5		Black ceramic	Ceramic
6		Black ceramic	Ceramic



No.	Photo of testing part	Parts Description	Client Claimed Material
7		Orange ceramic	Ceramic
8		Orange ceramic	Ceramic
9		Red ceramic	Ceramic
10		Black ceramic	Ceramic

==== End of Report =====