
Test Report

Report No. : AGC05443240418-001

SAMPLE NAME : 3 BBQ tools in pouch
MODEL NAME : MO8290
APPLICANT : MID OCEAN BRANDS B.V
STANDARD(S) : Please refer to the following page(s).
DATE OF ISSUE : Apr. 19, 2024

Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd.



Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.


Applicant : MID OCEAN BRANDS B.V
Address : 7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong.
Test Site : 6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community, Hangcheng Street, Bao'an District, Shenzhen, Guangdong, China

Report on the submitted sample(s) said to be:

Sample Name : 3 BBQ tools in pouch
Model : MO8290
Vendor code : 104438
Country of Origin : CHINA
Country of Destination : EUROPE
Sample Received Date : Apr. 12, 2024
Testing Period : Apr. 12, 2024 to Apr. 19, 2024
Test Requested : Selected test(s) as requested by client.

Test Requested:**Conclusion**

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 63 - Lead(Pb) Content	Pass
Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 23 -Cadmium(Cd) Content	Pass
Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 51&52 - Phthalates Content	Pass
Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50 - Polycyclic-aromatic Hydrocarbons (PAHs) Content	Pass
Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 43 - Aromatic Amines Azodyes (AZO) Content	Pass
Mechanical dishwashing safe test	Pass
- Colour fastness to rubbing	Pass
Regulation 1935/2004/EC and Technical Guide on Metals and alloys used in food contact materials of Council of Europe Resolution CM/Res(2013)9 - Specific migration of Heavy metal	Pass

Approved by: 

Suhongliang, Leon

Technical Director

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Report Revise Record

Report Version	Issued Date	Valid Version	Notes
/	Apr. 19, 2024	Valid	Initial release

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the “Dedicated Testing/Inspection Stamp” is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

The photo of the sample



The photo of AGC05443240418-001 is for use only with the original report.

Test Point Description

Test point	Test point description
1-1+1-2+1-3	Black cloth+ Black webbing+ Black edging fabric
1-4+1-5	Black zipper fabric+ Black elastic band
1-6	Black plastic zipper teeth
1-7	Metal zipper head
1-8+1-9+1-10	Metal clip+ Metal fork+ Metal shovel
1-11	Metal handle
1-12	Black cloth
1-13	Black webbing
1-14	Black edging fabric
1-15	Black zipper fabric
1-16	Black elastic band
1-17	Metal shovel

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the “Dedicated Testing/Inspection Stamp” is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Test Results:

Note: N.D.=Not Detected (less than method detection limit), MDL = Method Detection Limit, 1mg/kg=0.0001%

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 63
- Lead(Pb) Content

Test Methods and Equipment: IEC 62321-5:2013; ICP-OES

Test Item(s)	Unit	Limit	MDL	Test Result(s)		
				1-1+1-2+1-3	1-4+1-5	1-6
Lead(Pb)	mg/kg	500	10	22	N.D.	N.D.
Conclusion				Conformity	Conformity	Conformity

Test Item(s)	Unit	Limit	MDL	Test Result(s)		
				1-7	1-8+1-9+1-10	1-11
Lead(Pb)	mg/kg	500	10	17	N.D.	N.D.
Conclusion				Conformity	Conformity	Conformity

Remark:

1. As specified by client, the submitted samples were mixed to test, the test points: 1-1+1-2+1-3,1-4+1-5,1-8+1-9+1-10

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 23
-Cadmium(Cd) Content

Test Methods and Equipment: IEC 62321-5:2013; ICP-OES

Test Item(s)	Unit	Limit	MDL	Test Result(s)
				1-6
Cadmium(Cd)	mg/kg	100	10	N.D.
Conclusion				Conformity

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Attestation of Global Compliance(Shenzhen)Co., Ltd

Attestation of Global Compliance(Shenzhen)Std & Tech Co., Ltd

Tel: +86-755 2523 4088 E-mail: agc@agccert.com Web: http://www.agccert.com/

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 51&52
- Phthalates Content

Test Methods and Equipment: IEC 62321-8:2017; GC-MS

Test Item(s)	Unit	Limit	MDL	Test Result(s)
				1-6
Diisobutyl phthalate (DIBP) CAS:84-69-5	%	0.1	0.005	N.D.
Dibutyl phthalate (DBP) CAS:84-74-2	%	0.1	0.005	N.D.
Butylbenzyl phthalate (BBP) CAS:85-68-7	%	0.1	0.005	N.D.
Di-(2-ethylhexyl) Phthalate (DEHP) CAS:117-81-7	%	0.1	0.005	N.D.
Di-n-octyl phthalate (DNOP) CAS:117-84-0	%	/	0.005	N.D.
Di-isononyl phthalate (DINP) CAS:28553-12-0, 68515-48-0	%	/	0.005	N.D.
Di-isodecyl phthalate(DIDP) CAS:26761-40-0, 68515-49-1	%	/	0.005	N.D.
Sum of DIBP +DBP+BBP+DEHP	%	0.1	/	N.D.
Sum of DNOP+DINP+DIDP	%	0.1	/	N.D.
Conclusion				Conformity

Limit requirements of Phthalates

Toys and childcare articles	Each of DEHP, DBP, BBP, DIBP is less than 0.1% or the sum of DEHP+DBP+BBP+DIBP is less than 0.1%
Toys and childcare articles which can be placed in the mouth by children	The sum of DINP+DIDP+DNOP is less than 0.1%

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Attestation of Global Compliance(Shenzhen)Co., Ltd

Attestation of Global Compliance(Shenzhen)Std & Tech Co., Ltd

Tel: +86-755 2523 4088 E-mail: agc@agccert.com Web: http://www.agccert.com/

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50
- Polycyclic-aromatic Hydrocarbons (PAHs) Content

Test Methods and Equipment: Afps GS 2019:01 PAK; GC-MS

Test Item(s)	Unit	Limit	MDL	Test Result(s)
				1-6
Benzo[a]pyrene(BaP)	mg/kg	1	0.1	N.D.
Benzo[e]pyrene(BeP)	mg/kg	1	0.1	N.D.
Benzo[a]anthracene(BaA)	mg/kg	1	0.1	N.D.
Benzo[b]fluoranthene(BbF)	mg/kg	1	0.1	N.D.
Benzo[j]fluoranthene(BjFA)	mg/kg	1	0.1	N.D.
Benzo[k]fluoranthene(BkF)	mg/kg	1	0.1	N.D.
Chrysene(CHR)	mg/kg	1	0.1	N.D.
Dibenzo[a,h]anthracene(DBA)	mg/kg	1	0.1	N.D.
Conclusion				Conformity

Limit requirements of Polycyclic-aromatic Hydrocarbons (PAHs) (Unit: mg/kg)

Items	CAS No.	Extender oils or used for the production of tyres or parts of tyres	Any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity	Toys, including activity toys, and childcare articles, any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity
Benzo[a]pyrene(BaP)	50-32-8	≤ 1	≤ 1	≤ 0.5
Benzo[e]pyrene(BeP)	192-97-2	/	≤ 1	≤ 0.5
Benzo[a]anthracene(BaA)	56-55-3	/	≤ 1	≤ 0.5
Benzo[b]fluoranthene(BbF)	205-99-2	/	≤ 1	≤ 0.5
Benzo[j]fluoranthene(BjFA)	205-82-3	/	≤ 1	≤ 0.5
Benzo[k]fluoranthene(BkF)	207-08-9	/	≤ 1	≤ 0.5
Chrysene(CHR)	218-01-9	/	≤ 1	≤ 0.5
Dibenzo[a,h]anthracene(DBA)	53-70-3	/	≤ 1	≤ 0.5
Sum of BaP+ BeP+ BaA+ BbF+ BjFA+ BkF+ CHR+ DBA	/	≤ 10	/	/

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Attestation of Global Compliance(Shenzhen)Co., Ltd

Attestation of Global Compliance(Shenzhen)Std & Tech Co., Ltd

Tel: +86-755 2523 4088 E-mail: agc@agccert.com Web: http://www.agccert.com/

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 43
- Aromatic Amines Azodyes (AZO) Content

Test Methods and Equipment: EN ISO 14362-1:2017; GC-MS

Test Item(s)	Unit	Limit	MDL	Test Result(s)	
				1-1+1-2+1-3	1-4+1-5
4-Aminobiphenyl CAS:92-67-1	mg/kg	30	5	N.D.	N.D.
Benzidine CAS:92-87-5	mg/kg	30	5	N.D.	N.D.
4-Chloro-o-toluidine CAS:95-69-2	mg/kg	30	5	N.D.	N.D.
2-Naphthylamine CAS:91-59-8	mg/kg	30	5	N.D.	N.D.
o-Aminoazotoluene CAS:97-56-3	mg/kg	30	5	N.D.	N.D.
5-Nitro-o-toluidine CAS:99-55-8	mg/kg	30	5	N.D.	N.D.
p-Chloroaniline CAS:106-47-8	mg/kg	30	5	N.D.	N.D.
4-Methoxy-m-phenylenediamine CAS:615-05-4	mg/kg	30	5	N.D.	N.D.
4,4'-Diaminodiphenylmethane CAS:101-77-9	mg/kg	30	5	N.D.	N.D.
3,3'-Dichlorobenzidine CAS:91-94-1	mg/kg	30	5	N.D.	N.D.
3,3'-Dimethoxybenzidine CAS:119-90-4	mg/kg	30	5	N.D.	N.D.
3,3'-Dimethylbenzidine CAS:119-93-7	mg/kg	30	5	N.D.	N.D.
4,4'-Methylenedi-o-toluidine CAS:838-88-0	mg/kg	30	5	N.D.	N.D.
p-Cresidine CAS:120-71-8	mg/kg	30	5	N.D.	N.D.
4,4'-Methylenebis[2-chloroaniline] CAS:101-14-4	mg/kg	30	5	N.D.	N.D.
4,4'-Oxydianiline CAS:101-80-4	mg/kg	30	5	N.D.	N.D.
4,4'-Thiodianiline CAS:139-65-1	mg/kg	30	5	N.D.	N.D.
2-Aminotoluene CAS:95-53-4	mg/kg	30	5	N.D.	N.D.
2,4-Toluyldiamine CAS:95-80-7	mg/kg	30	5	N.D.	N.D.
2,4,5-Trimethylaniline CAS:137-17-7	mg/kg	30	5	N.D.	N.D.
o-Anisidine CAS:90-04-0	mg/kg	30	5	N.D.	N.D.
4-Aminoazobenzene CAS:60-09-3	mg/kg	30	5	N.D.	N.D.
Conclusion				Conformity	Conformity

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Attestation of Global Compliance(Shenzhen)Co., Ltd

Attestation of Global Compliance(Shenzhen)Std & Tech Co., Ltd

Tel: +86-755 2523 4088 E-mail: agc@agccert.com Web: http://www.agccert.com/

Remark:

1. As specified by client, the submitted samples were mixed to test, the test points: 1-1+1-2+1-3,1-4+1-5

Note: 4-aminoazobenzene: The EN ISO 14362-1:2017 or ISO 17234-1:2020 methods will enable further cleavage of 4-aminoazobenzene to aniline and / or 1,4-phenylenediamine. If aniline and / or 1,4-phenylenediamine are detected, 4-aminoazobenzene shall be further determined by EN ISO 14362-3:2017 or ISO 17234-2:2011.

Mechanical dishwashing safe test

Test Result of mechanical dishwashing safe test:
Requirements: For dishwasher safe test, if there is no noticeable change in appearance (e.g. color, size and shape) and function, it should be "PASS"
Sample No.:1-8/1-9/1-10/1-11 Test method: Refer BS EN 12875 -1-2005 Washing temperature: 60°C Number of cycle: 10 cycles Number of tested sample: 2 pc(s). Number of control sample: 1 pc(s).
For all tested plastic or metal articles: No visible change of color, gloss and clouding was found on the tested samples after wash. No visible deposit or iridescent layer was found on the tested samples after wash. No visible swelling, deformation, cracking, crazing or delamination was found on the tested samples after wash.

- Colour fastness to rubbing

Test Method: ISO 105-X12:2016

Rubbing finger: Cylinder

The time of conditioning as well as the atmospheric conditions during testing: 21.0 °C, 60 %R.H., 4 hrs

The percentage of soak of wet rubbing cloth: 95%~100%

The long direction of the specimen: Endwise/ Crossrange

Test point	Test Result		Conclusion
	Colour fastness to rubbing / (Grade)		
	Dry rubbing	Wet rubbing	
1-12	4-5	4-5	Conformity
1-13	4-5	4-5	Conformity
1-14	4-5	4-5	Conformity
1-15	4-5	4-5	Conformity
1-16	4-5	4-5	Conformity
Limit (Client's Requirement)	≥2-3	≥2-3	/

Note:

Colour Fastness Grade:

Grade 5 = No Colour Change (Best Grade)

Grade 1 = Colour Change Seriously (Bad Grade)

9 grades in gray sample card: 5, 4-5, 4, 3-4, 3, 2-3, 2, 1-2, 1.

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Attestation of Global Compliance(Shenzhen)Co., Ltd

Attestation of Global Compliance(Shenzhen)Std & Tech Co., Ltd

Tel: +86-755 2523 4088 E-mail: agc@agccert.com Web: http://www.agccert.com/

- Specific migration of Heavy metal


Test Item(s)	Test condition/ Equipment	MDL (mg/kg)	Test Result(s) (mg/kg)	Limit (mg/kg)	
			1-17		
			1 st + 2 nd extractives		
Barium (Ba)	0.5% Citric acid 70°C, 2h, ICP-OES	0.1	N.D.	8.4	
Copper (Cu)		0.1	N.D.	28	
Iron (Fe)		0.1	0.575	280	
Tin (Sn)		0.1	N.D.	700	
Chromium (Cr)		0.01	N.D.	1.75	
Manganese (Mn)		0.1	N.D.	12.6	
Zinc (Zn)		0.1	N.D.	35	
Aluminium (Al)		0.1	0.240	35	
Lithium (Li)		0.01	N.D.	0.336	
Beryllium (Be)		0.005	N.D.	0.07	
Vanadium (V)		0.005	N.D.	0.07	
Nickel (Ni)		0.01	N.D.	0.98	
Cobalt (Co)		0.01	N.D.	0.14	
Arsenic (As)		0.002	N.D.	0.014	
Molybdenum(Mo)		0.01	N.D.	0.84	
Silver (Ag)		0.01	N.D.	0.56	
Cadmium (Cd)		0.002	N.D.	0.035	
Antimony (Sb)		0.01	N.D.	0.28	
Mercury (Hg)		0.002	N.D.	0.021	
Thallium (Tl)		0.0001	N.D.	0.0007	
Lead (Pb)		0.01	N.D.	0.07	
Conclusion			/	Conformity	/
Magnesium (Mg)			0.01	0.045	/
Titanium (Ti)		0.01	N.D.	/	

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.


Test Item(s)	Test condition/ Equipment	MDL (mg/kg)	Test Result(s) (mg/kg)	Limit (mg/kg)	
			1-17		
			3 rd extractives		
Barium (Ba)	0.5% Citric acid 70°C, 2h, ICP-OES	0.1	N.D.	1.2	
Copper (Cu)		0.1	N.D.	4	
Iron (Fe)		0.1	N.D.	40	
Tin (Sn)		0.1	N.D.	100	
Chromium (Cr)		0.01	N.D.	0.25	
Manganese (Mn)		0.1	N.D.	1.8	
Zinc (Zn)		0.1	N.D.	5	
Aluminium (Al)		0.1	N.D.	5	
Lithium (Li)		0.01	N.D.	0.048	
Beryllium (Be)		0.005	N.D.	0.01	
Vanadium (V)		0.005	N.D.	0.01	
Nickel (Ni)		0.01	N.D.	0.14	
Cobalt (Co)		0.01	N.D.	0.02	
Arsenic (As)		0.002	N.D.	0.002	
Molybdenum(Mo)		0.01	N.D.	0.12	
Silver (Ag)		0.01	N.D.	0.08	
Cadmium (Cd)		0.002	N.D.	0.005	
Antimony (Sb)		0.01	N.D.	0.04	
Mercury (Hg)		0.002	N.D.	0.003	
Thallium (Tl)		0.0001	N.D.	0.0001	
Lead (Pb)		0.01	N.D.	0.01	
Conclusion			/	Conformity	/
Magnesium (Mg)			0.01	N.D.	/
Titanium (Ti)		0.01	N.D.	/	

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Test Flow Chart of Heavy Metal Content




Test Flow Chart of Phthalates



Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the “Dedicated Testing/Inspection Stamp” is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Test Flow Chart of Polycyclic-aromatic Hydrocarbons (PAHs)




Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the “Dedicated Testing/Inspection Stamp” is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Attestation of Global Compliance(Shenzhen)Co., Ltd

Attestation of Global Compliance(Shenzhen)Std & Tech Co., Ltd

Tel: +86-755 2523 4088 E-mail: agc@agccert.com Web: <http://www.agccert.com/>

Test Flow Chart of AZO



Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Conditions of Issuance of Test Reports

1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the “Company”) solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the “Clients”).
2. Any report issued by Company as a result of this application for testing services (the “Report”) shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.
3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.
4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.
5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.
6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations.
7. Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.
8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.
9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

*** End of Report ***

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the “Dedicated Testing/Inspection Stamp” is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.