

TEST REPORT

Report No	WTF23F03048422C
Applicant	Mid Ocean Brands B.V.
Address	7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan,
Manufacturer	Kowloon, Hong Kong 109623
Sample Name	Stoneware chalk mug
Sample Model	MO8658
Test Requested	 Client's requirements - BS EN 12875-4:2006 Mechanical dishwashing resistance of utensils - Part 4: Rapid test for domestic ceramic articles Client's requirements - BS EN 15284:2007 Test Method for the Resistance to Microwave Heating of Ceramic, Glass, Glass-Ceramic or Plastic Cookware
Test Conclusion	Refer to next page (s)
Date of Receipt sample	2023-03-14
Testing period	2023-03-14 to 2023-03-17
Date of Issue	2023-03-20
Test Result	Refer to next page (s)

Prepared By:

Waltek Testing Group (Foshan) Co., Ltd.

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Signed for and on behalf of Waltek Testing Group (Foshan) Co., Ltd.

Swing Liang

Swing.Liang

Waltek Testing Group (Foshan) Co., Ltd. http://www.waltek.com.cn

1/5

WT-F-510-3003-05-A

Report No.: WTF23F03048422C



Sample photo:







GG

D3) REP

Report No.: WTF23F03048422C

Test Result:

	e (D	S EN 12875-4:2006)
Test Standard	:	BS EN 12875-4:2006 Mechanical dishwashing resistance of utensils - Part 4: Rapid
t it it	5	test for domestic ceramic articles
Number of tested	n.	3 pcs per style for testing, 1 pc as control sample.
sample	A	the state state with which will be a state of
Procedure	Q.	1. Preparation of test specimens
	* ~1	1.1 Remove any surface contamination from the test specimens, e.g. by washing the specimens by hand in a mild liquid detergent at about 45°C, followed by rinsing and drying with a clean cloth.
	wint	1.2 Place the test specimens in the inspection site and examine them with normal corrected vision from a distance of (30 ± 10) cm, while the viewing angle is changed.
	NUTE	All test specimens of a given type shall be of comparable quality in gloss and colour; discard any specimens that are of inferior quality. Retain one specimen as an untested reference standard.
	ale.	2. Immersion of test specimens
	- JUN	2.1 Determine the surface area of the test specimens. Fill the tank with sufficient water to completely cover the specimens. Check for compliance with the surface area to volume criterion; if the calculated surface area approaches the critical limit of 130 cm ² /l, a greater volume shall be used.
	Nº1	2.2 Cover the tank and adjust the water bath temperature to give a test tank temperature of $(75\pm1)^{\circ}$ C. Record the tank temperature.
	5 A .	2.3 Add sufficient detergent to give a 0.5% solution in the test tank. Stir well to
	54	disperse the detergent. Immediately lower the test specimens, in the racks, into the tank and cover with the lid.
	at s	2.4 After 16h±10 min, record the temperature in the tank and remove the test specimens. Rinse the test specimens in hot water and rub dry with a clean cloth (the rubbing action will also remove any loose colour).
	m	2.5 Examine the specimens, comparing tested items with the corresponding untested reference standards and report any changes in gloss or colour using the method described in EN 12875-2.
	NUTE TEX	 2.6 Repeat the immersion procedure for a further 16h±10 min using fresh detergent solution. Remove the test specimens, rinse and dry them as described in 2.4. 2.7 Re-examine the specimens as described in 2.5 after a total of 32 hours
Test Result	: 3	PASS

Test Result:

SEX SEX NO	After	16 hours imme	rsion	After 32 hours immersion			
Test specimen	Gloss	Colour	Other aspects	Gloss	Colour	Other aspects	
white 1 white	0	0	<u></u>	0	1, 0 m	10 M	
2	5 ⁶⁵ 0,5 ⁶⁷	0,00	~n_ 0 ~n_	0	0	- 0	
3 3	0	0	<u></u> 0		me o me	~~~ 0 ~~~	

Waltek Testing Group (Foshan) Co., Ltd. http://www.waltek.com.cn



IK RT

Report No.: WTF23F03048422C

Note:

Rating			
No visible change			
first discernible change			
Clearly visible change			

2) Microwave Safe (BS EN 15284:2007)

Test Standard	: ,	BS EN 15284:2007
	no.	Test Method for the Resistance to Microwave Heating of Ceramic, Glass, Glass-
		Ceramic of Plastic Cookware
No. of Specimen	550	3 pieces for testing, Remains as control samples.
Test Requirement :		1. Ceramic items shall display no signs of cracking, crazing, scaling or colour.
		2. Glass, Glass ceramic items shall display no signs of cracking, scaling or colour.
		3. Plastic items shall display no signs of cracking, colour, melting, deformation, suitability for re-use of charring.
	-sur	 4. The maximum surface temperature of handles (if applicable) after the short period heating shall not exceed: a. Ceramic, Glass, Glass-ceramic = 56°C
ex white white	MALI	b. Plastic = 60° C
Conclusion(s)		PASS, Details as following
1. No visible damage	ge wa	as found on all tested samples after testing.
2. No arcing was of	bserv	ved on all tested samples during testing.
3. Surface tempera	ture	at the handle of the tested samples did not exceed the maximum as specified by the

standard (see test data).

Test Data:

Tool Doried	Location	Highes	st Temperatu	Deminent	
Test Period		Sample 1	Sample 2	Sample 3	Requirement
After the Short Period	Handle	32.0	35.9	36.9	Ceramic, Glass or Glass-ceramic ≤ 56°C
Heating	Surface of body	38.9	39.8	41.3	
After the Long Period	Handle	81.4	79.7	75.2	+ 15 15th 5th
Heating	Surface of body	91.2	93.3	87.6	an ar an

Description for Specimen:

Specimen No.	Specimen Description			
sint man 12 min w	White black stoneware chalk mug (Overall individual)			

Waltek Testing Group (Foshan) Co., Ltd. http://www.waltek.com.cn

Report No.: WTF23F03048422C



Remarks:

- 1. The results shown in this test report refer only to the sample(s) tested;
- 2. This test report cannot be reproduced, except in full, without prior written permission of the company;
- 3. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver;
- 4. The Applicant name and Address, the sample(s) and sample information was/were provided by the applicant who should be responsible for the authenticity which Waltek hasn't verified;
- 5. If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.
- 6. The sample material information (Model No. information) is provided by client, not verified by test laboratory. The samples of reference Model No. are not tested. Test laboratory not responsible for the accuracy, appropriateness, completeness and authenticity of the information provided by client.

===== End of Report ======

