

TEST REPORT

Report No. : WTF23F03040786C

Applicant: Mid Ocean Brands B.V.

Address: 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan,

Kowloon, Hong Kong

Manufacturer..... 111025

Sample Name...... 250ml porcelain conic mug

Sample Model : MO9078

dishwashing resistance of utensils - Part 4: Rapid test for

domestic ceramic articles

2) Client's requirements - BS EN 15284:2007 Materials and

articles in contact with food stuffs for the resistance to

microwave heating of ceramic, glass, glass-ceramic or plastic

cookware

Test Conclusion : Refer to next page (s)

Date of Receipt sample 2023-03-06

Testing period...... 2023-03-06 to 2023-03-15

Date of Issue 2023-03-16

Test Result : Refer to next page (s)

Prepared By:

Waltek Testing Group (Foshan) Co., Ltd.

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China

Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Signed for and on behalf of

Waltek Testing Group (Foshan) Co., Ltd.

Swing Liang

Swing.Liang



Sample photo:



MANUAL INTERPRETATION



Test Results:

1) Dishwasher Safe (BS EN 12875-4:2006)

Number of tested : sample Procedure :	test for domestic ceramic articles 3 pcs per style for testing, 1 pc as control sample.
sample	3 pcs per style for testing, 1 pc as control sample.
Procedure :	the test the state with the the the
Whitek wh	1. Preparation of test specimens 1.1 Remove any surface contamination from the test specimens, e.g. by washing the specimens by hand in a mild liquid detergent at about 45°C, followed by rinsing and drying with a clean cloth. 1.2 Place the test specimens in the inspection site and examine them with normal corrected vision from a distance of (30±10) cm, while the viewing angle is changed. All test specimens of a given type shall be of comparable quality in gloss and colour; discard any specimens that are of inferior quality. Retain one specimen as an untested reference standard. 2. Immersion of test specimens 2.1 Determine the surface area of the test specimens. Fill the tank with sufficient water to completely cover the specimens. Check for compliance with the surface area to volume criterion; if the calculated surface area approaches the critical limit of 130 cm²/l, a greater volume shall be used. 2.2 Cover the tank and adjust the water bath temperature to give a test tank temperature of (75±1)°C. Record the tank temperature. 2.3 Add sufficient detergent to give a 0.5% solution in the test tank. Stir well to disperse the detergent. Immediately lower the test specimens, in the racks, into the tank and cover with the lid. 2.4 After 16h±10 min, record the temperature in the tank and remove the test specimens. Rinse the test specimens in hot water and rub dry with a clean cloth (the rubbing action will also remove any loose colour). 2.5 Examine the specimens, comparing tested items with the corresponding untested reference standards and report any changes in gloss or colour using the method described in EN 12875-2. 2.6 Repeat the immersion procedure for a further 16h±10 min using fresh detergent solution. Remove the test specimens, rinse and dry them as described in 2.4.
Test Result :	2.7 Re-examine the specimens as described in 2.5 after a total of 32 hours PASS

Test Result:

Test specimen	After	16 hours imme	ersion	After 32 hours immersion			
	Gloss	Colour	Other aspects	Gloss	Colour	Other aspects	
July 1 July	111 0 111	0	0	- 10 mi	no O m	40 4	
2 2	JE 0 JE	MITE ON OUT	m 0 m	0	0	- O+ 3	
30 4	0	0	10 July	J 0 J	10 m	m 0 m	



Note:

Classification	Rating No visible change		
1 0 pt 1 50 50			
Will Mari Mr. My And And	first discernible change		
2 1 1 10	Clearly visible change		

2) Microwave Safe (BS EN 15284:2007)

2) Microwave Sate) (B2	S EN 15284:2007)		
Test Standard	:	BS EN 15284:2007		
The state of the s	alle.	Test Method for the Resistance to Microwave Heating of Ceramic, Glass, Glass-		
"		Ceramic of Plastic Cookware		
No. of Specimen	ين الم	3 pieces for testing, Remains as control samples.		
Test Requirement :		1. Ceramic items shall display no signs of cracking, crazing, scaling or colour.		
at at	E.F.	2. Glass, Glass ceramic items shall display no signs of cracking, scaling or colour.		
write while and		3. Plastic items shall display no signs of cracking, colour, melting, deformation,		
	6.	suitability for re-use of charring.		
TEX LIER OLIV	715	4. The maximum surface temperature of handles (if applicable) after the short period		
11/2 11.	100	heating shall not exceed:		
e et et	4	a. Ceramic, Glass, Glass-ceramic = 56°C		
E. WILL MULL	aller.	b. Plastic = 60°C		
Conclusion(s)	2	PASS, Details as following		

- 1. No visible damage was found on all tested samples after testing.
- 2. No arcing was observed on all tested samples during testing.
- 3. Surface temperature at the handle of the tested samples did not exceed the maximum as specified by the standard (see test data).

Test Data:

Test Period	Location	Highes	st Temperatu	Doguiroment		
Test Fellou	Location	Sample 1	Sample 2	Sample 3	Requirement	
After the Short Period	Handle	38.8	39.5	38.2	Ceramic, Glass or Glass-ceramic ≤ 56°C	
Heating	Surface of body	57.3	56.7	57.6		
After the Long Period	Handle	76.3	74.9	72.1	of the little the	
Heating	Surface of body	82.9	78.3	77.6	mr W m	

Description for Specimen:

Specimen No.	Specimen Description		
LIFE WALTER WILLE WALL W	White porcelain conic mug (Overall individual)		



Remarks:

- 1. The results shown in this test report refer only to the sample(s) tested;
- 2. This test report cannot be reproduced, except in full, without prior written permission of the company;
- 3. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver;
- 4. The Applicant name and Address, the sample(s) and sample information was/were provided by the applicant who should be responsible for the authenticity which Waltek hasn't verified;
- 5. If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.
- 6. The sample material information (Model No. information) is provided by client, not verified by test laboratory. The samples of reference Model No. are not tested. Test laboratory not responsible for the accuracy, appropriateness, completeness and authenticity of the information provided by client.

===== End of Report =====



