



TEST REPORT

Report No. : WTF23F05110192T
Applicant..... : Mid Ocean Brands B.V.
Address..... : 7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong
Manufacturer : 111999
Sample Name : Mug with spoon and top bamboo
Sample Model..... : MO9708
Test Requested : In accordance with Regulation (EU) No 10/2011, Council of Europe Resolution AP(2002)2, Council of Europe Resolution 84/500/EC (2005/31/EC) and Regulation (EC) No 1935/2004.
Test Conclusion : **Pass** (Please refer to next pages for details)
Date of Receipt sample : 2023-05-22
Testing period : 2023-05-22 to 2023-05-29
Date of Issue..... : 2023-05-29
Test Result..... : Refer to next page (s)

Prepared By:

Waltek Testing Group (Foshan) Co., Ltd.

Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City,
Chencun, Shunde District, Foshan, Guangdong, China
Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Signed for and on behalf of
Waltek Testing Group (Foshan) Co., Ltd.

Jessise Liu

Jessise.Liu



Report No.: WTF23F05110192T

Test Results:

1. Specific Migration of Formaldehyde

Test Item	Result (mg/kg)	LOQ (mg/kg)	Limit (mg/kg)
	No.1		
Migration of Formaldehyde	7	1	15

Note:

1. Test Method: With reference to BS EN 13130-1: 2004, sample preparation in 3% acetic acid at 70°C for 2 hours, analysis was performed by UV-visible Spectrometer.
2. "mg/kg" = milligram per kilogram
3. LOQ = Limit of quantitation
4. ND = Not Detected or lower than limit of quantitation
5. The specification was quoted from regulation (EU) No 10/2011.

2. Pentachlorophenol (PCP) Content

Test Item	Result (mg/kg)	LOQ (mg/kg)	Limit (mg/kg)
	No.1		
Pentachlorophenol (PCP)	ND	0.10	0.15

Note:

1. Test method: With reference to LFGB § 64 BVL B 82.02.8-2001, analysis was performed by GC-MS.
2. "mg/kg" = milligram per kilogram
3. LOQ = Limit of quantitation
4. ND = Not Detected or lower than limit of quantitation
5. The specification was quoted from Council of Europe Resolution AP(2002)2.



Report No.: WTF23F05110192T

3. Extractable Lead and Cadmium Content

Test Items	Result (mg/L)	LOQ (mg/L)	Limit (mg/L)
	No.2		
Extractable Lead	ND	0.1	4.0
Extractable Cadmium	ND	0.02	0.3

Test Items	Result (mg/dm ²)	LOQ (mg/dm ²)	Limit (mg/dm ²)
	No.3		
Extractable Lead	ND	0.1	0.8
Extractable Cadmium	ND	0.02	0.07

Note:

1. Test method: With reference to BS EN 1388-1: 1996 and BS EN 1388-2: 1996, sample preparation in 4% acetic acid at 22±2°C for 24 hours, analysis was performed by ICP-MS.
2. "mg/L" = milligram per litre
3. "mg/dm²" = milligram per square decimetre
4. LOQ = Limit of quantitation
5. ND = Not Detected, less than limit of quantitation
6. The specification was quoted from 84/500/EC (2005/31/EC).

WALTEK



Report No.: WTF23F05110192T

Sample Photo:




Photograph of parts tested:

No.	Photo of testing part	Parts Description	Client Claimed Material
1		Wood	Wood
2		White ceramic	Ceramic



Report No.: WTF23F05110192T

No.	Photo of testing part	Parts Description	Client Claimed Material
3		White ceramic	Ceramic

Remarks:

1. The results shown in this test report refer only to the sample(s) tested;
2. This test report cannot be reproduced, except in full, without prior written permission of the company;
3. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver;
4. The Applicant name and Address, the sample(s) and sample information was/were provided by the applicant who should be responsible for the authenticity which Waltek hasn't verified;
5. If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.

===== End of Report =====